LIEBHERR

CONSTRUCTION EQUIPMENT



LIEBHERR L580 069050-1760 - Front Left Wheel Hub

Sample No: LH0240411

Oil Type: LIEBHERR GEAR BASIC 90 LS

_					
JSAM	PLE INFO	RMATION			
Sample Number		LH0240411	LH0240389	LH0240378	
Sample Date		15 Sep 2023	08 Mar 2023	13 Dec 2022	
Machine Hours		4000	2000	1005	
Oil Hours		0	0	0	
Oil Changed		Changed	Changed	Changed	
Sample Status		ATTENTION	NORMAL	NORMAL	
<u> </u>					
OILC	ONDITIO	N			
/isc @ 40°C	cSt	① 186	O 182	194	
L	331	O 100	0 .0=		
CON	TAMINA	TION			
Silicon	ppm	15	0 8	3 3	
Sodium	ppm	5	O 1	6	
otassium	ppm	() <1	0	O <1	
Ö WEA					
WEA	R METAI	LS			
ron	ppm	247	78	O 271	
Copper	ppm	<u>0</u> 189	105	184	
_ead	ppm	<u> </u>	3	O 5	
īn	ppm	<u> </u>	6	13	
Aluminum	ppm	1	O <1	O 2	
Chromium	ppm	1	O <1	3	
Nolybdenum	ppm	0 0	0	0	
lickel	ppm	() <1	O <1	02	
itanium	ppm	0	0	<1	
Silver	ppm	0	0	0	
Manganese	ppm	11	8	56	
/anadium	ppm	0	0	<1	
MIL.					
ADD	ITIVES				
Calcium	ppm	6	6	9	
/lagnesium	ppm	0 2	O 3	O 3	
Zinc	ppm	O 141	33	O 81	
Phosphorus	ppm	2460	2521	2352	
Barium	ppm	0 <1	0 0	0 0	
Boron	ppm	0 2	01	0 2	
			_	_	



PRODUITS FORESTIERS D.G. LTEE 313 RANG ST-JOSEPH STE-AURELIE, QC

CA G0M 1M0
Contact: Roger .

T: (418)593-3547 F: (418)593-3633

Diagnosis

We recommend an early resample to monitor this condition.Lead ppm levels are noted. Copper and tin ppm levels are marginal. All other component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot:PRO9STEUnique No:5645579Signed:Bill QuesnelReport Date:22 Sep 2023





GRAPHS

