## LIEBHERR

**CONSTRUCTION EQUIPMENT** 

### LIEBHERR L506 051669 - Diesel Engine

Sample No: LH0261005

Oil Type: PETRO CANADA 10W30

<u> </u>				
SAM	<b>PLE INF</b>	ORMATION		
Sample Number		LH0261005	 	
Sample Date		14 Dec 2023	 	
Machine Hours		2322	 	
Oil Hours		0	 	
Oil Changed		N/A	 	
Sample Status		MARGINAL	 	
OILC	ONDITI	ON		
Visc @ 100°C	cSt	<b>12.6</b>	 	
Oxidation (PA)	%	76	 	
CON	ramin.	TION		

CONTAMINATION					
Water	%	<b>0.111</b>			
Soot %	%	<b>0</b> 0			***
Nitration (PA)	%	87			
Sulfation (PA)	%	56			
Glycol	%	<b>0.0</b>			
Fuel	%	<1.0			
Silicon	ppm	<b>4</b>			
Sodium	ppm	<b>4</b>			
Potassium	ppm	<b>2</b>			

WE!	AR META	LS		
Iron	ppm	<b>8</b>	 	
Copper	ppm	<b>0</b> <1	 	
Lead	ppm	<b>0</b>	 	
Tin	ppm	<b>0</b>	 	
Aluminum	ppm	<b>3</b>	 	
Chromium	ppm	<b>()</b> <1	 	
Molybdenum	ppm	<b>44</b>	 	
Nickel	ppm	<b>0</b> <1	 	
Titanium	ppm	0	 	
Silver	ppm	<b>0</b> 0	 	
Manganese	ppm	<b>0</b> 0	 	
Vanadium	ppm	0	 	

ADDITIVES					
Calcium	ppm	<b>1190</b>			
Magnesium	ppm	<b>822</b>			
Zinc	ppm	<b>1152</b>			
Phosphorus	ppm	<b>1015</b>			
Barium	ppm	<b>0</b>			
Boron	ppm	<b>71</b>			

Report Id: LBADOL [WCAMIS] 02615880 (Generated: 02/16/2024 10:24:22) Rev: 1





#### LIEBHERR CANADA LTEE

444 AVENUE DE LA FRICHE DOLBEAU-MISTASSINI, QC CA G8L 3M7

Contact: Martin Gagnon martin.gagnon@liebherr.com

T:

F: (418)276-9844

#### Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is a trace of moisture present in the oil. Test for glycol is negative. The condition of the oil is acceptable for the time in service.

Depot:LBADOLUnique No:5732990Signed:Kevin MarsonReport Date:16 Feb 2024

# LIEBHERR

CONSTRUCTION EQUIPMENT





#### **GRAPHS**

