## LIEBHERR

**CONSTRUCTION EQUIPMENT** 



Sample No: LH

Oil Type: GEAR OIL SAE 80W90

SAMPLE INFORMATION							
Sample Number	LH	LH	LH0250095	LH0242828			
Sample Date	15 Feb 2024	17 Sep 2023	27 Mar 2023	31 Oct 2022			
Machine Hours	5100	4000	2020	2020			
Oil Hours	0	0	0	0			
Oil Changed	Changed	N/A	N/A	N/A			
Sample Status	NORMAL	NORMAL	NORMAL	NORMAL			

	OIL CO	NDITION			
√isc @	40°C	cSt	<b>186</b>	<b>181</b>	<b>178</b>

CON	TAMIN	ATION				
Water	%	NEG	NEG	NEG	NEG	
Silicon	ppm	<b>○</b> <1	O <1	O <1	O <1	
Sodium	ppm	<b>○</b> <1	O 2	O 2	O 2	
Potassium	nnm	0 -1	0 -1	0	0	

(O) WEA					
WEA	R METALS				
Iron	ppm	<b>2</b>	O 2	O 2	<b>3</b>
Copper	ppm	<b>○</b> <1	<b>3</b>	O 1	<b>5</b>
Lead	ppm	<b>0</b>	0	O <1	O <1
Tin	ppm	<b>0</b>	0	0	0
Aluminum	ppm	<b>0</b> <1	O <1	O 0	<b>0</b>
Chromium	ppm	<b>0</b>	0	O 0	0
Molybdenum	ppm	<b>0</b>	O 0	O 0	<b>0</b>
Nickel	ppm	<b>0</b>	O <1	O <1	O <1
Titanium	ppm	0	0	0	0
Silver	ppm	0	<1	0	0
Manganese	ppm	<b>0</b>	O 0	<b></b> <1	O <1
Vanadium	ppm	0	0	0	0

vanadium	ppm	0	0	U	U
ADD	ITIVES				
Calcium	ppm	<b>2</b>	O 14	<b>8</b>	0 8
Magnesium	ppm	<b>O</b> <1	O <1	<1	0
Zinc	ppm	<b>3</b>	<b>4</b>	O 5	<b>6</b>
Phosphorus	ppm	<b>2355</b>	O 2476	2530	O 2453
Barium	ppm	<b>0</b>	O	O	<b>6</b>
Boron	ppm	<1	O <1	<b>1</b>	O 1



Industrial Metals 550 Messier St. Winnipeg, MB CA R2J 0G5

Contact: Service Manager

T: F:

## Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot:IND550WINUnique No:5733878Signed:Wes DavisReport Date:20 Feb 2024

**CONSTRUCTION EQUIPMENT** 





## **GRAPHS**

