# LIEBHERR

# **CONSTRUCTION EQUIPMENT**



## [(355228) [50241076]] LIEBHERR LH60M 114198-1217 - Swing

Sample No: LH0290538

Oil Type: PETRO CANADA TRAXON 75W90 SYNTHETIC

5					
Sam	ple Info	rmation			
Sample Number		LH0290538	LH0225134	LH0224846	
Sample Date		11 Jul 2024	07 Dec 2023	18 Nov 2022	
Machine Hours		10000	8004	4073	
Oil Hours		0	0	0	
Oil Changed		Changed	Changed	Changed	
Sample Status		NORMAL	NORMAL	NORMAL	
Oil	onditio	1			
Visc @ 40°C	cSt	<b>99.6</b>	O 105	O 103	
Cont	taminat	ion			
147 .	0/	NEO	NEO	NIEO	

Contamination								
Water	%	NEG	NEG	NEG				
Silicon	ppm	<b>3</b>	<b>6</b>	O <1				
Sodium	ppm	<b>1</b>	<b>3</b>	O 2				
Potassium	ppm	<b>0</b> <1	O 2	<b>1</b>				

Wear	Metals				
Iron	ppm	<b>76</b>	<b>8</b> 4	<b>5</b> 3	
Copper	ppm	<b>18</b>	<b>24</b>	O 27	
Lead	ppm	<b>0</b>	<b></b> <1	O <1	
Tin	ppm	<b>0</b>	O <1	O <1	
Aluminum	ppm	<b>0</b> <1	<b></b> <1	O 0	
Chromium	ppm	<b>0</b> <1	O <1	O <1	
Molybdenum	ppm	<b>0</b>	0	O 0	
Nickel	ppm	<b>0</b> <1	O <1	O <1	
Titanium	ppm	0	0	0	
Silver	ppm	0	0	0	
Manganese	ppm	<b>()</b> <1	O <1	O <1	
Vanadium	ppm	0	0	0	

Additives						
Calcium	ppm	<b>15</b>	O 13	<b>7</b>		
Magnesium	ppm	<b>2</b>	O 2	O 2		
Zinc	ppm	<b>14</b>	<b>9</b>	O 12		
Phosphorus	ppm	<b>1244</b>	O 1238	995		
Barium	ppm	<b>4</b>	O 15	O 0		
Boron	ppm	<b>303</b>	O 285	O 154		



AltaSteel
9401 34 St NW
Edmonton, AB
CA T6B 2X6
Contact: Richard Bailey
richard.bailey@altasteel.com

T: F:

#### Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot:ALT940EDMUnique No:5814324Signed:Wes DavisReport Date:18 Jul 2024

**CONSTRUCTION EQUIPMENT** 





### **Graphs**

