

LIEBHERR

CONSTRUCTION EQUIPMENT



LIEBHERR LH60M 1204-75634 - Rear Left Wheel Hub

Sample No: LH0243411

Oil Type: LIEBHERR GEAR BASIC 90 LS



AMERICAN STATE EQUIPMENT CO.
 2400 NORTH 14TH AVENUE
 WAUSAU, WI
 US 54401
 Contact: CHRIS BARTNIK
 cbartnik@amstate.com
 T: (715)675-6900
 F: (715)675-9748



SAMPLE INFORMATION

Sample Number	LH0243411	LH0207661	LH0185366	LHMC133346
Sample Date	10 Aug 2023	16 Mar 2022	27 Aug 2021	06 Dec 2019
Machine Hours	15947	15048	13973	11965
Oil Hours	0	0	0	0
Oil Changed	Changed	Changed	Changed	Changed
Sample Status	NORMAL	NORMAL	NORMAL	NORMAL



OIL CONDITION

Visc @ 40°C	cSt	177	197	187	130
-------------	-----	-----	-----	-----	-----



CONTAMINATION

Silicon	ppm	0	<1	<1	<1
Sodium	ppm	2	3	3	<1
Potassium	ppm	0	0	0	8



WEAR METALS

Iron	ppm	5	8	8	4
Copper	ppm	1	2	6	5
Lead	ppm	0	0	0	0
Tin	ppm	0	0	0	0
Aluminum	ppm	0	<1	0	0
Chromium	ppm	0	<1	<1	<1
Molybdenum	ppm	0	<1	<1	1
Nickel	ppm	0	0	<1	0
Titanium	ppm	0	0	0	1
Silver	ppm	0	<1	0	0
Manganese	ppm	0	<1	<1	<1
Vanadium	ppm	0	0	0	0



ADDITIVES

Calcium	ppm	12	2	10	75
Magnesium	ppm	2	<1	4	26
Zinc	ppm	7	1	10	48
Phosphorus	ppm	2372	2338	2065	1609
Barium	ppm	0	0	<1	0
Boron	ppm	1	12	50	274

Diagnosis


Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot: LEC0008
 Unique No: 10608962
 Signed: Sean Felton
 Report Date: 21 Aug 2023




GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C

