LIEBHERR

CONSTRUCTION EQUIPMENT

LIEBHERR LH60C1528-132602-Left Final Drive

Sample No: LH0210067

Oil Type: TEXACO HAVOLINE GEAR OIL 80W90

_					
JSAM	PLE INFOR	MATION			
Sample Number		LH0210067	LH0210058	LH0210049	LH0210040
Sample Date		22 Sep 2023	04 Apr 2023	06 Jan 2023	24 May 2022
Machine Hours		5266	4009	3384	1995
Oil Hours		0	0	0	0
Oil Changed		Changed	Changed	Changed	Changed
Sample Status		ABNORMAL	ABNORMAL	ABNORMAL	ABNORMAL
<u> </u>		71211011111111			
OILC	ONDITION				
Visc @ 40°C	cSt	133	O 141	O 174	O 148
طد				-	
CON	TAMINATI	ON			
Silicon	ppm	<u> </u>	O 324	O 253	<u>145</u>
Sodium	ppm	3	O 5	4	5
Potassium	ppm	13	O 26	2 1	O 12
WEA	R METALS				
Iron	ppm	575	O 722	592	384
Copper	ppm	24	O 28	28	○ 33
Lead	ppm	2	6	5	4
Tin	ppm	1	0 1	02	2
Aluminum	ppm	44	9 1	6 7	36
Chromium	ppm	6	6	5	4
Molybdenum	ppm	() <1	O 2	6	○ 18
Nickel	ppm	4	6	4	O <1
Titanium	ppm	4	7	7	5
Silver	ppm	0	0	0	4
Manganese	ppm	5	6	6	4
Vanadium	ppm	0	<1	<1	0
ADD	ITIVES				
Calcium	ppm	215	403	○ 352	O 217
Magnesium	ppm	26	46	43	49
Zinc	ppm	22	29	57	60
Phosphorus	ppm	489	O 427	477	○ 835
Barium	ppm	0	O 2	O 0	0 8
Boron	ppm	3	7	17	5



STAIMAN RECYCLING
201 HEPBURN ST
WILLIAMSPORT, PA
US 17701
Contact: JOE MARKLEY
jmarkleysr@staimanrecycling.com
T: (570)419-5479
F:

Diagnosis

We advise that you check all areas where dirt can enter the system. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. Gear wear is indicated. Elemental levels of silicon (Si) and aluminum (Al) indicate alumina-silicate (coarse dirt) ingress. The condition of the oil is acceptable for the time in service.

Depot: STAWILLH
Unique No: 10672315
Signed: Don Baldridge
Report Date: 03 Oct 2023

CONSTRUCTION EQUIPMENT





GRAPHS

