LIEBHERR
CONSTRUCTION EQUIPMENT

[[BALL CONTRACTORS]] CATERPILLAR 3126 - Port Diesel Engi

Sample No: LH0267316

Oil Type: SAE 30W

LIEBHERR EQUIPMENT SOURCE
10119 RESIDENCY ROAD
MANASSAS, VA
US 20110
Contact: TOM HEINEY
tom.heiney@liebherr.com
T: (703)392-0111
F: (703)331-5604

SAMPLE INFORMATION

Sample Number		**LH0267316**	---	---	---
Sample Date		**28 Dec 2023**	---	---	---
Machine Hours		**2100**	---	---	---
Oil Hours		**150**	---	---	---
Oil Changed		**Not Changd**	---	---	---
Sample Status		**NORMAL**	---	---	---

OIL CONDITION

Visc @ 100°C	cSt	**9.6**	---	---	---
Base Number (BN)	mg KOH/g	**6.8**	---	---	---
Oxidation (PA)	%	**33**	---	---	---

CONTAMINATION

Water	%	**NEG**	---	---	---
Soot %	%	**0.2**	---	---	---
Nitration (PA)	%	**48**	---	---	---
Sulfation (PA)	%	**43**	---	---	---
Glycol	%	**NEG**	---	---	---
Fuel	%	**<1.0**	---	---	---
Silicon	ppm	**7**	---	---	---
Sodium	ppm	**2**	---	---	---
Potassium	ppm	**0**	---	---	---

WEAR METALS

Iron	ppm	**20**	---	---	---
Copper	ppm	**8**	---	---	---
Lead	ppm	**<1**	---	---	---
Tin	ppm	**<1**	---	---	---
Aluminum	ppm	**1**	---	---	---
Chromium	ppm	**<1**	---	---	---
Molybdenum	ppm	**34**	---	---	---
Nickel	ppm	**<1**	---	---	---
Titanium	ppm	**<1**	---	---	---
Silver	ppm	**0**	---	---	---
Manganese	ppm	**<1**	---	---	---
Vanadium	ppm	**<1**	---	---	---

ADDITIVES

Calcium	ppm	**1765**	---	---	---
Magnesium	ppm	**83**	---	---	---
Zinc	ppm	**899**	---	---	---
Phosphorus	ppm	**789**	---	---	---
Barium	ppm	**1**	---	---	---
Boron	ppm	**17**	---	---	---

Diagnosis

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Depot: LIEBHERRVA
Unique No: 10831434
Signed: Wes Davis
Report Date: 16 Jan 2024

LIEBHERR
CONSTRUCTION EQUIPMENT

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number