

LIEBHERR

CONSTRUCTION EQUIPMENT



LIEBHERR LH50 1216-116574 - Rear Right Wheel Hub

Sample No: LH0272157

Oil Type: GEAR OIL SAE 80W90



SAMPLE INFORMATION

Sample Number	LH0272157	LH0171140	LH0171114	LH0171112
Sample Date	20 Dec 2023	29 Aug 2023	27 Apr 2023	27 Jan 2023
Machine Hours	19776	17910	16726	14930
Oil Hours	0	0	0	0
Oil Changed	Changed	Changed	Changed	Changed
Sample Status	NORMAL	NORMAL	NORMAL	NORMAL

BOISE WHITE PAPER

3RD AVE AND HWY 11, 400 2ND ST
INTERNATIONAL FALLS, MN
US 56649
Contact: GARY MANN
garymann@packagingcorp.com
T:
F: (218)285-5860



OIL CONDITION

Visc @ 40°C	cSt	127	142	181	152



CONTAMINATION

Water	%	NEG	NEG	NEG	NEG
Silicon	ppm	3	3	5	9
Sodium	ppm	2	3	3	3
Potassium	ppm	0	0	2	0



WEAR METALS

Iron	ppm	51	82	89	202
Copper	ppm	12	15	13	51
Lead	ppm	0	0	0	2
Tin	ppm	<1	0	0	0
Aluminum	ppm	0	<1	<1	2
Chromium	ppm	0	0	0	1
Molybdenum	ppm	3	2	0	<1
Nickel	ppm	0	0	0	<1
Titanium	ppm	<1	<1	0	0
Silver	ppm	0	0	0	0
Manganese	ppm	<1	1	2	4
Vanadium	ppm	0	<1	0	0



ADDITIVES

Calcium	ppm	97	39	14	56
Magnesium	ppm	18	6	2	4
Zinc	ppm	44	16	10	47
Phosphorus	ppm	767	1089	2257	1818
Barium	ppm	0	0	0	2
Boron	ppm	22	23	28	164

Diagnosis

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.


All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot: BOIINT
Unique No: 10844604
Signed: Wes Davis
Report Date: 23 Jan 2024




GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C

