## LIEBHERR

**CONSTRUCTION EQUIPMENT** 



Sample No: LH0220354

Oil Type: LIEBHERR GEAR BASIC 90 LS

<b>5</b>				
SAM	PLE INFOR	MATION		
Sample Number		LH0220354	 	
Sample Date		23 Oct 2023	 	
Machine Hours		500	 	
Oil Hours		0	 	
Oil Changed		N/A	 	
Sample Status		NORMAL	 	
OILC	ONDITION			
Visc @ 40°C	cSt	<b>163</b>	 	

CON	TAMIN	ATION		
Water	%	NEG	 	
Silicon	ppm	<b>2</b>	 	
Sodium	ppm	<b>2</b>	 	
Potassium	ppm	<b>()</b> <1	 	

WEA	R METALS	5		
Iron	ppm	<b>2</b>	 	
Copper	ppm	<b>9</b>	 	
Lead	ppm	<b>0</b>	 	
Tin	ppm	<b>0</b>	 	
Aluminum	ppm	<b>2</b>	 	
Chromium	ppm	<b>0</b> <1	 	
Molybdenum	ppm	<b>0</b>	 	
Nickel	ppm	<b>0</b>	 	
Titanium	ppm	0	 	
Silver	ppm	0	 	
Manganese	ppm	<b>0</b>	 	
Vanadium	ppm	0	 	

Vanadium	ppm	0	 	
WII.				
ADE	DITIVES			
Calcium	ppm	<b>10</b>	 	
Magnesium	ppm	<b>O</b> <1	 	
Zinc	ppm	<b>0</b>	 	
Phosphorus	ppm	<b>1370</b>	 	
Barium	ppm	<b>191</b>	 	
Boron	ppm	<b>75</b>	 	



ADVANTAGE METALS RECYCLING - ST LOUIS 5 N MARKET ST LOUIS, MO

US 63102 Contact: JEANETTE VAGO

jeanette.vago@advantagerecycling.com

T: F:

## Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot:ADVSTLUnique No:10849980Signed:Sean FeltonReport Date:31 Jan 2024

## LIEBHERR







## **GRAPHS**

