

# LIEBHERR

## CONSTRUCTION EQUIPMENT



### LIEBHERR R956 056876-1728 - Right Final Drive

Sample No: LH0258537

Oil Type: LIEBHERR GEAR BASIC 90 LS



**FINKBINER EQUIPMENT CO.**  
 15 W 400 N FRONTAGE RD  
 BURR RIDGE, IL  
 US 60527  
 Contact: DON FITZGERALD  
 dfitzgerald@finkbiner.com  
 T: (815)546-8991  
 F: (630)654-3792



#### SAMPLE INFORMATION

Sample Number	LH0258537	---	---	---
Sample Date	12 Feb 2024	---	---	---
Machine Hours	1075	---	---	---
Oil Hours	1000	---	---	---
Oil Changed	Changed	---	---	---
Sample Status	NORMAL	---	---	---



#### OIL CONDITION

Visc @ 40°C	cSt	● 198	---	---	---
-------------	-----	-------	-----	-----	-----



#### CONTAMINATION

Water	%	NEG	---	---	---
Silicon	ppm	● 10	---	---	---
Sodium	ppm	● 0	---	---	---
Potassium	ppm	● 0	---	---	---



#### WEAR METALS

Iron	ppm	● 272	---	---	---
Copper	ppm	● <1	---	---	---
Lead	ppm	● 0	---	---	---
Tin	ppm	● 0	---	---	---
Aluminum	ppm	● 2	---	---	---
Chromium	ppm	● 4	---	---	---
Molybdenum	ppm	● 0	---	---	---
Nickel	ppm	● <1	---	---	---
Titanium	ppm	<1	---	---	---
Silver	ppm	0	---	---	---
Manganese	ppm	● 3	---	---	---
Vanadium	ppm	0	---	---	---



#### ADDITIVES

Calcium	ppm	● 24	---	---	---
Magnesium	ppm	● 4	---	---	---
Zinc	ppm	● 10	---	---	---
Phosphorus	ppm	● 1095	---	---	---
Barium	ppm	● 2	---	---	---
Boron	ppm	● 0	---	---	---

#### Diagnosis

Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot: LEC0033  
 Unique No: 10899463  
 Signed: Don Baldrige  
 Report Date: 28 Feb 2024




### GRAPHS

#### Ferrous Alloys



#### Non-ferrous Metals



#### Viscosity @ 40°C

