CONSTRUCTION EQUIPMENT

LIEBHERR LH60 115240-1529 - Swing Drive

Sample No: LHMC122143

Oil Type: LIEBHERR GEAR BASIC 90 LS

Sample Information

Sample Number	LHMC122143	LH0272834	LHMC104499	LHMC116230			
Sample Date	17 Apr 2024	20 Dec 2023	22 Mar 2023	29 Sep 2022			
Machine Hours	5177	4719	3682	2906			
Oil Hours	485	686	0	0			
Oil Changed	Changed	Changed	Not Changd	Not Changd			
Sample Status	ABNORMAL	NORMAL	NORMAL	NORMAL			
Oil Condition							
Visc @ 40°C cSt	208	0 168	0 161	128			

Con	ntaminati	ion				
Water	%	0.556	NEG	NEG	NEG	
Silicon	ppm	06	0 2	03	5	
Sodium	ppm	0 29	◯ <1	0	9	
Potassium	ppm	0 2	01	◯ <1	◯ <1	

Wear	Metals				
Iron	ppm	347	274	0 16	0 182
Copper	ppm	0 89	25	2	0 44
Lead	ppm	0	○ <1	○ <1	0
Tin	ppm	04	3	0	○ <1
Aluminum	ppm	○ <1	○ <1	0	01
Chromium	ppm	3	0 4	0	○ <1
Molybdenum	ppm	07	3	0	2
Nickel	ppm	01	○ <1	0	0
Titanium	ppm	0	<1	0	0
Silver	ppm	<1	0	0	0
Manganese	ppm	3	2	○ <1	2
Vanadium	ppm	0	0	0	<1

¢ **Additives** Calcium ppm 93 18 0 147 02 2 Magnesium 09 2 $\bigcirc 4$ ppm Zinc 070 06 0 150 0 12 ppm Phosphorus ppm 0 2059 0 1726 887 0 511 Barium 03 ppm $\bigcirc 0$ $\bigcirc 0$ $\bigcirc 0$ Boron ppm 0 12 $\bigcirc 7$ $\bigcirc 0$ 1





DAVIS INDUSTRIAL INC.

9920 RICHMOND HIGHWAY LORTON, VA US 22079 Contact: JAMIE jamie.davisindustries@gmail.com T: F:

Diagnosis

We advise that you check for the source of water entry. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.Moderate concentration of visible metal present. All component wear rates are normal. There is a moderate concentration of water present in the oil. The condition of the oil is acceptable for the time in service.

Depot:DAVLORVAUnique No:10992562Signed:Jonathan HesterReport Date:25 Apr 2024Contact/Location:JAMIE ? - DAVLORVA





Graphs

O

