

LIEBHERR

CONSTRUCTION EQUIPMENT



LIEBHERR LH60M 1204-74217 - Front Right Wheel Hub

Sample No: LH0268898

Oil Type: LIEBHERR GEAR BASIC 90 LS



MIDDLE RIVER MARINE
 1771 SOUTH TORRENCE AVE
 CHICAGO, IL
 US 60617
 Contact: Scott Molitor
 scottmolitor@gomiddleriver.com
 T:
 F:



Sample Information

Sample Number	LH0268898	LHMC121033	LHMC92418	LHMC80526
Sample Date	09 Apr 2024	10 Aug 2017	31 Mar 2017	24 May 2016
Machine Hours	14693	8752	7383	4556
Oil Hours	1000	0	0	0
Oil Changed	Changed	Changed	Changed	Changed
Sample Status	NORMAL	NORMAL	ATTENTION	ABNORMAL



Oil Condition

Visc @ 40°C	cSt	126	177.2	275.3	175.3
-------------	-----	-----	-------	-------	-------



Contamination

Water	%	NEG	NEG	NEG	NEG
Silicon	ppm	2	2	2	4
Sodium	ppm	<1	<1	<1	3
Potassium	ppm	0	8	0	6



Wear Metals

Iron	ppm	6	165	221	462
Copper	ppm	<1	23	32	58
Lead	ppm	0	<1	0	0
Tin	ppm	0	<1	0	0
Aluminum	ppm	0	2	2	3
Chromium	ppm	0	2	2	5
Molybdenum	ppm	0	0	2	0
Nickel	ppm	0	<1	0	1
Titanium	ppm	0	0	<1	<1
Silver	ppm	0	0	0	0
Manganese	ppm	<1	2	3	7
Vanadium	ppm	0	0	0	0



Additives

Calcium	ppm	8	11	12	12
Magnesium	ppm	0	<1	1	2
Zinc	ppm	0	19	20	45
Phosphorus	ppm	801	1032	396	1012
Barium	ppm	0	31	67	302
Boron	ppm	59	156	1	2

Diagnosis


Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The condition of the oil is acceptable for the time in service.

Depot: MIDCHIL
 Unique No: 11004469
 Signed: Don Baldrige
 Report Date: 01 May 2024




Graphs

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C

