


Machine Id
DRYER DEPT 4 (S/N 03715)
Component
Reciprocating Compressor
Fluid
FRIGOSPEC (16 LTR)



DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION method limit/base current history1 history2

Sample Number	Client Info	PC0061758	PC0051886	PC0022582
Sample Date	Client Info	18 Oct 2022	27 Oct 2021	18 Oct 2020
Machine Age	hrs Client Info	0	0	0
Oil Age	hrs Client Info	0	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

WEAR METALS method limit/base current history1 history2

PQ	ASTM D8184*		0	0	0
Iron	ppm ASTM D5185(m)	>50	<1	3	2
Chromium	ppm ASTM D5185(m)	>10	0	<1	0
Nickel	ppm ASTM D5185(m)		<1	0	0
Titanium	ppm ASTM D5185(m)		0	0	0
Silver	ppm ASTM D5185(m)		0	<1	0
Aluminum	ppm ASTM D5185(m)	>25	0	<1	<1
Lead	ppm ASTM D5185(m)	>25	0	0	0
Copper	ppm ASTM D5185(m)	>50	0	<1	<1
Tin	ppm ASTM D5185(m)	>15	0	<1	0
Antimony	ppm ASTM D5185(m)		<1	<1	<1
Vanadium	ppm ASTM D5185(m)		0	0	0
Beryllium	ppm ASTM D5185(m)		0	0	0
Cadmium	ppm ASTM D5185(m)		0	0	0

ADDITIVES method limit/base current history1 history2

Boron	ppm ASTM D5185(m)		<1	<1	<1
Barium	ppm ASTM D5185(m)		0	0	0
Molybdenum	ppm ASTM D5185(m)		0	0	0
Manganese	ppm ASTM D5185(m)		0	0	0
Magnesium	ppm ASTM D5185(m)		0	0	<1
Calcium	ppm ASTM D5185(m)		0	0	0
Phosphorus	ppm ASTM D5185(m)		0	0	<1
Zinc	ppm ASTM D5185(m)		<1	<1	<1
Sulfur	ppm ASTM D5185(m)		27	17	27
Lithium	ppm ASTM D5185(m)		<1	<1	<1






CONTAMINANTS method limit/base current history1 history2

Silicon	ppm ASTM D5185(m)	>25	0	0	<1
Sodium	ppm ASTM D5185(m)		0	0	0
Potassium	ppm ASTM D5185(m)	>20	<1	<1	<1
Water	% ASTM D6304*	>0.1	0.001	---	---
ppm Water	ppm ASTM D6304*	>1000	10.5	---	---

FLUID DEGRADATION method limit/base current history1 history2

Acid Number (AN)	mg KOH/g ASTM D974*		0.02	0.02	0.02
------------------	---------------------	--	-------------	------	------

OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	70.0	68.7	67.0
Visc @ 100°C	cSt	ASTM D7279(m)	7.2	8.9	8.7
Viscosity Index (VI)	Scale	ASTM D2270*	39	102	101

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS	
<p>Ferrous Alloys</p>	<p>PQ</p>
<p>Non-ferrous Metals</p>	<p>Acid Number</p>
<p>Viscosity @ 40°C</p>	



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0061758 **Received** : 19 Oct 2022
Lab Number : **02517158** **Diagnosed** : 20 Oct 2022
Unique Number : 5474138 **Diagnostician** : Kevin Marson
Test Package : IND 2 (Additional Tests: KF, KV100, TAN Man, VI)

SAPUTO FOODS LTD
 284 HOPE STREET WEST
 TAVISTOCK, ON
 CA N0B 2R0
 Contact: Joseph Ross
 joseph.ross@saputo.com
 T: (519)655-2337
 F: (519)655-3449

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.