

### **OIL ANALYSIS REPORT**

#### Sample Rating Trend

NORMAL

# REINTJES CAL012 (S/N K84269)

**Reduction Gear** 

#### Mobilgear 600 XP 150 (600 LTR)

#### DIAGNOSIS

#### Recommendation

Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

Additive levels indicate the addition of a different brand, or type of oil. The condition of the oil is acceptable for the time in service.

			May2022	0ct2022		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PC0011791	PC0052748	
Sample Date		Client Info		03 Oct 2022	18 May 2022	
Machine Age	hrs	Client Info		16509	0	
Oil Age	hrs	Client Info		16509	0	
Oil Changed		Client Info		Not Changd	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINATI	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>150	7	6	
Chromium	ppm	ASTM D5185(m)	>10	0	0	
Nickel	ppm	ASTM D5185(m)	>10	<1	0	
Titanium	ppm	ASTM D5185(m)		0	0	
Silver	ppm	ASTM D5185(m)		0	0	
Aluminum	ppm	ASTM D5185(m)	>25	<1	0	
Lead	ppm	ASTM D5185(m)	>100	3	2	
Copper	ppm	ASTM D5185(m)	>50	10	7	
Tin	ppm	ASTM D5185(m)	>10	1	1	
Antimony	ppm	ASTM D5185(m)	>5	0	<1	
Vanadium	ppm	ASTM D5185(m)		0	0	
Beryllium	ppm	ASTM D5185(m)		0	0	
Cadmium	ppm	ASTM D5185(m)		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		17	11	
Barium	ppm	ASTM D5185(m)		0	0	
Molybdenum	ppm	ASTM D5185(m)		0	0	
Manganese	ppm	ASTM D5185(m)		<1	<1	
Magnesium	ppm	ASTM D5185(m)		9	8	
Calcium	ppm	ASTM D5185(m)		39	35	
Phosphorus	ppm	ASTM D5185(m)		358	318	
Zinc	ppm	ASTM D5185(m)		27	23	
Sulfur	ppm	ASTM D5185(m)		10023	9605	
Lithium	ppm	ASTM D5185(m)		<1	<1	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	0	<1	
Sodium	ppm	ASTM D5185(m)		2	1	
Potassium	ppm	ASTM D5185(m)	>20	<1	<1	





## **OIL ANALYSIS REPORT**


VICLIAI

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.







	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	Visual*	NONE	NONE	NONE	
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
	Precipitate	scalar	Visual*	NONE	NONE	NONE	
	Silt	scalar	Visual*	NONE	NONE	NONE	
	Debris	scalar	Visual*	NONE	NONE	NONE	
	Sand/Dirt	scalar	Visual*	NONE	VLITE	NONE	
	Appearance	scalar	Visual*	NORML	NORML	NORML	
	Odor	scalar	Visual*	NORML	NORML	NORML	
	Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	
	Free Water	scalar	Visual*		NEG	NEG	
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D7279(m)	150	145	144	
	Visc @ 100°C	cSt	ASTM D7279(m)	15.8	14.3	14.2	
	Viscosity Index (VI)	Scale	ASTM D2270*	98	95	95	
	SAMPLE IMAG	SES	method	limit/base	current	history1	history2
	Color						no image
	Color						no image
	Bottom						no image
	GRAPHS						
	Iron (ppm)				Lead (ppm)		
	400 Severe		400	Severe			
	E 200 - Abnormal			<u>E</u> 200	Abnormal		
	May 18/22			0ct3/22	May18/22		C., C. ***
	≥ Aluminum (ppm)				≥ Chromium (pr	om)	
	100			40		,	
	Severe				Severe		
	E 50 - Abnormal			<u>8</u> 20	Severe Abnormal		
	E. 50 -				Abnormal		5
	E. 50 -			0013/22 0			
	Copper (ppm)			0043/22	Abnormal		04-322
	Copper (ppm)			200	Silicon (ppm)		205-00
	Copper (ppm)			0043/22	Silicon (ppm)		construction of the second sec
	Copper (ppm)			200 200 <u>E</u> 100 <u>E</u> 100	Abremal Silicon (ppm)		22
	Copper (ppm)			200	Silicon (ppm)		044327
	Copper (ppm)			200 200 <u>E</u> 100 <u>E</u> 100	Abremal Silicon (ppm)		
	Copper (ppm)			200 201 201 201 201 201 201 201	Additives		
	Copper (ppm)			200 <u><u><u></u></u> <u><u></u></u> <u><u></u></u> <u><u></u></u> <u></u> <u></u> <u></u> <u></u></u>	Additives		

T:

F: