

OIL ANALYSIS REPORT

Sample Rating Trend



ELIOS U1-32

Component **Hydraulic System**

PETRO CANADA PURITY FG HYDRAULIC AW 68 (500 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PC0077155		
Sample Date		Client Info		01 Apr 2023		
Machine Age	hrs	Client Info		42783		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>20	3		
Chromium	ppm	ASTM D5185(m)	>20	0		
Nickel	ppm	ASTM D5185(m)	>20	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>20	0		
Lead	ppm	ASTM D5185(m)	>20	0		
Copper	ppm	ASTM D5185(m)	>20	<1		
Tin	ppm	ASTM D5185(m)	>20	0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1		
Barium	ppm	ASTM D5185(m)		0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		<1		
Calcium	ppm	ASTM D5185(m)		9		
Phosphorus	ppm	ASTM D5185(m)		341		
Zinc	ppm	ASTM D5185(m)		22		
Sulfur	ppm	ASTM D5185(m)		1945		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	4		
Sodium	ppm	ASTM D5185(m)		3		
Potassium	ppm	ASTM D5185(m)	>20	1		
FLUID CLEAN	INESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	191		
Particles >6µm		ASTM D7647	>1300	77		
Particles >14µm		ASTM D7647	>160	18		
Particles >21µm		ASTM D7647	>40	4		
Particles >38µm		ASTM D7647	>10	1		
Derticles 71		ASTM D7647	>3	0		
Particles >71µm						
Oil Cleanliness		ISO 4406 (c)	>19/17/14	15/13/11		
	DATION	ISO 4406 (c) method	>19/17/14 limit/base	15/13/11 current	 history1	history2


Acid Number (AN) mg KOH/g ASTM D974* 0.26 Report Id: IMLSTP [WCAMIS] 02569390 (Generated: 07/13/2023 09:01:05) Rev: 1


Contact/Location: Corinna Bouchard - IMLSTP



OIL ANALYSIS REPORT







	VISUAL		method				history2
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
	Precipitate	scalar	Visual*	NONE	NONE		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
Apr1/23	Appearance	scalar	Visual*	NORML	NORML		
Ap	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.05	NEG		
	Free Water	scalar	Visual*		NEG		
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D7279(m)	63.34	63.2		
	Visc @ 100°C	cSt	ASTM D7279(m)	8.409	8.7		
	Viscosity Index (VI)	Scale	ASTM D2270*	102	110		
23	SAMPLE IMAG	ES	method	limit/base	current	history1	history2
Apr1/23	Color					no image	no image
	Bottom					no image	no image
	GRAPHS	•					·
	Ferrous Alloys			491,52	Particle Count		т26
	B B Chromium chromium nickel			122,88 30,72 5,68 2,7,68 2,7,68 2,7,68 1,92 1,92	Severe 20 - 30 Abnormal		-24 -22 -20 -18 -16 -14 -14 -12
	₹ Non-ferrous Metal	5		April 2017 April 2017			16
	¹⁰ T			jo 12			
	8 - copper			mper			+14
	a 4			- 3	30-		-12
	2				8-		+10
				23	2+		
	Apr1/23			Apr1/23	-		
				-		4μ 21μ	38µ 71µ
	Viscosity @ 40°C				Acid Number		
	Abnormai			HOX 0.2	Base		
	ු 70 - දි 65 - Base ස්			ڦ ^{0.1}	8-		
				0.0 0.1 0.1 0.1 0.0 0.0 0.0 0.0 0.0 0.0	2		
	Abnormal			20.0			
	4pr1/23			Apr1/23	Apr1/23		20 June 193
	Apr			Apr	Apr		
boratory imple No. b Number ique Number st Package	: 02569390	Receive Diagnos Diagnos	d : 12 . ed : 13 . tician : We	ington, ON I Jul 2023 Jul 2023 s Davis	L7L 5H9 N	2	IML Containe 625, Route 34 St. Placide, QC CA JOV 28 orinna Bouchard

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

itact: Corinna Bouchard cbouchard@iml.ca T: (450)258-3130 F: (450)258-3345

Accredited Laboratory