




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

9258

Component

Natural Gas Engine

Fluid

PETRO CANADA DURON GEO LD 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0085923	GFL0072837	GFL0059995
Sample Date	Client Info		04 Jul 2023	16 Feb 2023	29 Sep 2022
Machine Age	hrs	Client Info	17061	15984	0
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	N/A	Changed
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >45	18	23	12
Chromium	ppm	ASTM D5185(m) >4	2	3	<1
Nickel	ppm	ASTM D5185(m) >4	<1	1	<1
Titanium	ppm	ASTM D5185(m) >5	0	<1	<1
Silver	ppm	ASTM D5185(m) >3	0	0	0
Aluminum	ppm	ASTM D5185(m) >25	5	6	2
Lead	ppm	ASTM D5185(m) >45	5	5	3
Copper	ppm	ASTM D5185(m) >175	3	2	1
Tin	ppm	ASTM D5185(m) >4	<1	<1	<1
Antimony	ppm	ASTM D5185(m)	0	0	<1
Vanadium	ppm	ASTM D5185(m)	0	0	0
Beryllium	ppm	ASTM D5185(m)	0	0	0
Cadmium	ppm	ASTM D5185(m)	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 50	14	6	6
Barium	ppm	ASTM D5185(m) 5	0	0	0
Molybdenum	ppm	ASTM D5185(m) 50	58	57	55
Manganese	ppm	ASTM D5185(m) 0	<1	1	<1
Magnesium	ppm	ASTM D5185(m) 560	662	627	600
Calcium	ppm	ASTM D5185(m) 1510	1755	1783	1647
Phosphorus	ppm	ASTM D5185(m) 780	902	845	781
Zinc	ppm	ASTM D5185(m) 870	1021	985	974
Sulfur	ppm	ASTM D5185(m) 2040	2038	2104	2063
Lithium	ppm	ASTM D5185(m)	<1	<1	<1

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >25	5	5	17
Sodium	ppm	ASTM D5185(m)	12	14	8
Potassium	ppm	ASTM D5185(m) >20	10	14	3
Glycol	%	ASTM D7922*	0.0	0.0	---

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	0	0	0
Nitration	Abs/cm	ASTM D7624*	13.2	7.2	11.9
Sulfation	Abs/.1mm	ASTM D7415*	28.2	19.7	24.4

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*	26.7	12.8	20.3











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	15.1	15.3	14.7

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 GFL Environmental - 554 - Edmonton SW
Sample No. : GFL0085923 **Received** : 13 Jul 2023
Lab Number : 02569626 **Diagnosed** : 14 Jul 2023
Unique Number : 5606672 **Diagnostician** : Kevin Marson
Test Package : MOB 1 (Additional Tests: Glycol)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

8409 -15th Street NW
 Edmonton, AB
 CA T6P 0B8
 Contact: Antonio De Rosa
 atheros@gflenv.com
 T: (780)509-2640
 F: (780)444-8851