

OIL ANALYSIS REPORT

Sample Rating Trend






Rear Hydraulic System Fluid


PETRO CANADA HYDREX XV ALL SEASON HYDRAULIC OIL (84 LTR)

DIAGNOSIS	SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Recommendation	Sample Number		Client Info		GFL0087347		
Resample at the next service interval to monitor. (Sample Date		Client Info		19 Jul 2023		
Customer Sample Comment: Oil sampleed,	Machine Age	hrs	Client Info		6950		
possibly. Hydro advanced 10, SAE10)	Oil Age	hrs	Client Info		1000		
Wear	Oil Changed		Client Info		Not Changd		
All component wear rates are normal.	Sample Status				NORMAL		
Contamination The system cleanliness is acceptable for your target	WEAR METALS	6	method	limit/base	current	history1	history2
ISO 4406 cleanliness code. The system and fluid	Iron	ppm	ASTM D5185(m)	>20	19		
cleanliness is acceptable.	Chromium	ppm	ASTM D5185(m)	>10	<1		
Fluid Condition	Nickel	ppm	ASTM D5185(m)		0		
The condition of the oil is acceptable for the time in	Titanium	ppm	ASTM D5185(m)		<1		
service.	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>10	2		
	Lead	ppm	ASTM D5185(m)		<1		
	Copper	ppm	ASTM D5185(m)		4		
	Tin	ppm	ASTM D5185(m)		0		
	Antimony	ppm	ASTM D5185(m)		0		
	Vanadium	ppm	ASTM D5185(m)		0		
	Beryllium	ppm	ASTM D5185(m)		0		
	Cadmium	ppm	ASTM D5185(m)		0		
	ADDITIVES		method	limit/base	current	history1	history2
	Boron	ppm	ASTM D5185(m)	0	1		
	Barium	ppm	ASTM D5185(m)		0		
	Molybdenum	ppm	ASTM D5185(m)		<1		
	Manganese	ppm	ASTM D5185(m)		<1		
	Magnesium	ppm	ASTM D5185(m)		6		
	Calcium	ppm	ASTM D5185(m)		357		
	Phosphorus	ppm	ASTM D5185(m)	670	784		
	Zinc	ppm	ASTM D5185(m)	850	928		
	Sulfur	ppm	ASTM D5185(m)	1600	1984		
	Lithium	Lithium ppm ASTM D5185(m) <1					
	CONTAMINANTS method limit/base current	history1	history2				
	Silicon	ppm	ASTM D5185(m)	>20	8		
	Sodium	ppm	ASTM D5185(m)		1		
	Potassium	ppm	ASTM D5185(m)	>20	2		
	FLUID CLEANL	INESS	method	limit/base	current	history1	history2
	Particles >4µm		ASTM D7647	>5000	2645		
	Particles >6µm		ASTM D7647	>1300	197		
	Particles >14µm		ASTM D7647		11		
	Particles >21µm		ASTM D7647	>40	3		
	Particles >38µm		ASTM D7647		0		
	Particles >71µm		ASTM D7647	>3	0		
	Oil Cleanliness		ISO 4406 (c)		19/15/11		
			()				




OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
Vhite Metal	scalar	Visual*	NONE	NONE		
ellow Metal	scalar	Visual*	NONE	NONE		
recipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
ppearance	scalar	Visual*	NORML	NORML		
Ddor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.1	NEG		
ree Water	scalar	Visual*		NEG		
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
/isc @ 40°C	cSt	ASTM D7279(m)	47.9	44.8		
SAMPLE IMAG	GES	method	limit/base	current	history1	history2
Color					no image	no image
				0		
Bottom				C. C. TRUE	no image	no image
GRAPHS						
Ferrous Alloys				Particle Coun	t	
			491,52	¹ T		T ²⁶
chromium			122,880			-24
nickel				Severe		
			30,72			-22
				Abnormal		-20
Jul 19/23			Jul19/23 (per 1 ml)			10
llul			lluc 1,521		•	-18
Non-ferrous Meta	ls		10 11 11 11 10 10			-16
copper 1			12 12		`	-14
Internet lead			Ling 1,920 Ling 1,920			11
tin j			31		\	-12
						10
Jul19/23			Jul19/23	2		-8
-			Inf	4μ 6μ		
Viscosity @ 40°C				4μ 6μ	14μ 21μ	38µ 71µ
Abnormal						
Base						
			_			
Abnormal			_			
9/23			Jul19/23			
Jul19/23			Jult			
WearCheck - C8-1				.7L 5H9 GFL Env		
GFL0087347)2572406	Receive Diagnos		Jul 2023 Jul 2023			Lafleche Roa ose Creek, O
5617457	Diagnos		in Marson		IVIC	CA KOC 1W
017437	Diagnos	LICIAII . INC.	111 111 111 111 111 111			



Validity of results and interpretation are based on the sample and information as supplied.

F: