



OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
432000
 Component
Natural Gas Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (--- GAL)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0085852	---	---
Sample Date	Client Info		14 Aug 2023	---	---
Machine Age	hrs	Client Info	2213	---	---
Oil Age	hrs	Client Info	1200	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			NORMAL	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >50	11	---	---
Chromium	ppm	ASTM D5185(m) >4	<1	---	---
Nickel	ppm	ASTM D5185(m) >2	0	---	---
Titanium	ppm	ASTM D5185(m)	0	---	---
Silver	ppm	ASTM D5185(m) >3	0	---	---
Aluminum	ppm	ASTM D5185(m) >9	2	---	---
Lead	ppm	ASTM D5185(m) >30	4	---	---
Copper	ppm	ASTM D5185(m) >35	5	---	---
Tin	ppm	ASTM D5185(m) >4	1	---	---
Antimony	ppm	ASTM D5185(m)	0	---	---
Vanadium	ppm	ASTM D5185(m)	0	---	---
Beryllium	ppm	ASTM D5185(m)	0	---	---
Cadmium	ppm	ASTM D5185(m)	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 50	12	---	---
Barium	ppm	ASTM D5185(m) 5	<1	---	---
Molybdenum	ppm	ASTM D5185(m) 50	59	---	---
Manganese	ppm	ASTM D5185(m) 0	<1	---	---
Magnesium	ppm	ASTM D5185(m) 560	515	---	---
Calcium	ppm	ASTM D5185(m) 1510	1550	---	---
Phosphorus	ppm	ASTM D5185(m) 780	687	---	---
Zinc	ppm	ASTM D5185(m) 870	859	---	---
Sulfur	ppm	ASTM D5185(m) 2040	1973	---	---
Lithium	ppm	ASTM D5185(m)	<1	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >+100	15	---	---
Sodium	ppm	ASTM D5185(m)	4	---	---
Potassium	ppm	ASTM D5185(m) >20	<1	---	---

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	11.2	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	25.0	---

FLUID DEGRADATION


	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*	>25	20.3	---

VISUAL

	method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.1	NEG	---
Free Water	scalar	Visual*		NEG	---











OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	15.1	14.0	---	---

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **GFL Environmental - 209 - Hamilton**
Sample No. : GFL0085852 **Received** : 17 Aug 2023 **560 Seaman Street**
Lab Number : **02576396** **Diagnosed** : 17 Aug 2023 **Stoney Creek, ON**
Unique Number : 5629456 **Diagnostician** : Wes Davis **CA L8E 3X7**
Test Package : MOB 1 **Contact: Fred Carleton**

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

fred.carleton@gflenv.com

T: (289)925-6693

F: (905)664-9008