




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
913136
 Component
Front Diesel Engine
 Fluid
PETRO CANADA DURON SHP 10W30 (38 LTR)

DIAGNOSIS

Recommendation

Échantillonner de nouveau l'équipement au prochain intervalle de vidange afin d'en surveiller la condition.

Wear

Les taux d'usure de tous les composants sont normaux.

Contamination

Il n'y a aucun indice de contamination dans l'huile.

Fluid Condition

L'état de l'huile est acceptable pour la durée de service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0079106	GFL0079109	GFL0079115
Sample Date	Client Info		28 Aug 2023	27 Jun 2023	27 Mar 2023
Machine Age	hrs	Client Info	1414	918	495
Oil Age	hrs	Client Info	496	423	495
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	0.6	0.6
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185(m)	>120	15	15	34
Chromium	ppm	ASTM D5185(m)	>20	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	8	8	14
Titanium	ppm	ASTM D5185(m)	>2	<1	<1	<1
Silver	ppm	ASTM D5185(m)	>2	<1	1	1
Aluminum	ppm	ASTM D5185(m)	>20	2	2	6
Lead	ppm	ASTM D5185(m)	>40	2	5	3
Copper	ppm	ASTM D5185(m)	>330	65	197	123
Tin	ppm	ASTM D5185(m)	>15	2	2	4
Antimony	ppm	ASTM D5185(m)		0	0	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)	2	13	33	236
Barium	ppm	ASTM D5185(m)	0	0	0	<1
Molybdenum	ppm	ASTM D5185(m)	50	71	73	110
Manganese	ppm	ASTM D5185(m)	0	<1	1	5
Magnesium	ppm	ASTM D5185(m)	950	664	641	651
Calcium	ppm	ASTM D5185(m)	1050	1431	1427	1553
Phosphorus	ppm	ASTM D5185(m)	995	1013	1009	715
Zinc	ppm	ASTM D5185(m)	1180	1154	1114	783
Sulfur	ppm	ASTM D5185(m)	2600	2475	2589	2020
Lithium	ppm	ASTM D5185(m)		<1	<1	<1

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m)	>25	6	11	58
Sodium	ppm	ASTM D5185(m)		2	1	4
Potassium	ppm	ASTM D5185(m)	>20	3	2	7

INFRA-RED


	method	limit/base	current	history1	history2	
Soot %	%	ASTM D7844*	>4	0.3	0.2	0
Nitration	Abs/cm	ASTM D7624*	>20	9.3	9.1	9.4
Sulfation	Abs/.1mm	ASTM D7415*	>30	21.3	19.9	27.5

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	ASTM D7414*	>25	15.3	15.5	22.6











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	12.00	11.3	11.2

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0079106 **Received** : 31 Aug 2023
Lab Number : 02579651 **Diagnosed** : 31 Aug 2023
Unique Number : 5632711 **Diagnostician** : Wes Davis
Test Package : MOB 1

Matrec - 791 - Rimouski
 350 Avenue de L'Industrie
 Rimouski, QC
 CA G5M 1W4
 Contact: Vincent Maltais
 info@foretsstar.com
 T: 4(18)388-2626
 F: (418)388-2038

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.