




OIL ANALYSIS REPORT

Sample Rating Trend

ISO



Machine Id
926051
Component
Hydraulic System
Fluid
NOT GIVEN (--- GAL)

DIAGNOSIS

Recommendation

Nous vous recommandons de vérifier tous les endroits par lesquels des contaminants peuvent pénétrer dans le système. Nous vous recommandons de remplacer le filtre et d'utiliser un système de filtrage hors-ligne afin d'améliorer la propreté du fluide. Le reniflard d'air doit être réparé. S'il n'est pas classé, nous vous recommandons de le remplacer par un reniflard à air adapté au micron et / ou au dessiccant. Si évalué, nous vous recommandons de réparer / remplacer le reniflard. Échantillonner de nouveau dans 30 à 45 jours afin de contrôler la situation. Le fluide n'était pas spécifié, toutefois, une comparaison avec d'autres fluides indiquent que ce fluide est du ISO 22 AW Hydraulic Oil. Veuillez confirmer la viscosité de l'huile et veuillez préciser la marque de votre prochain échantillon.

Wear

Le taux d'étain est marginal. Les taux d'usure de tous les autres composants sont normaux.

Contamination

Il y a une quantité élevée de matières particulaires (2 à 100 µm de taille) présente dans l'huile.

Fluid Condition

La viscosité de l'échantillon se situe dans la portée de l'ISO 22; nous vous conseillons de vérifier. l'huile peut encore servir si la contamination peut être réduite à un niveau acceptable.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0080337	---	---
Sample Date	Client Info		29 Aug 2023	---	---
Machine Age	kms	Client Info	404880	---	---
Oil Age	kms	Client Info	0	---	---
Oil Changed	Client Info		Not Chngd	---	---
Sample Status			SEVERE	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>50	28	---
Chromium	ppm	ASTM D5185(m)	>10	2	---
Nickel	ppm	ASTM D5185(m)	>4	0	---
Titanium	ppm	ASTM D5185(m)		<1	---
Silver	ppm	ASTM D5185(m)		0	---
Aluminum	ppm	ASTM D5185(m)	>5	2	---
Lead	ppm	ASTM D5185(m)	>4	0	---
Copper	ppm	ASTM D5185(m)	>15	1	---
Tin	ppm	ASTM D5185(m)	>4	▲ 4	---
Antimony	ppm	ASTM D5185(m)		0	---
Vanadium	ppm	ASTM D5185(m)		0	---
Beryllium	ppm	ASTM D5185(m)		0	---
Cadmium	ppm	ASTM D5185(m)		0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1	---
Barium	ppm	ASTM D5185(m)		0	---
Molybdenum	ppm	ASTM D5185(m)		<1	---
Manganese	ppm	ASTM D5185(m)		<1	---
Magnesium	ppm	ASTM D5185(m)		49	---
Calcium	ppm	ASTM D5185(m)		93	---
Phosphorus	ppm	ASTM D5185(m)		360	---
Zinc	ppm	ASTM D5185(m)		408	---
Sulfur	ppm	ASTM D5185(m)		790	---
Lithium	ppm	ASTM D5185(m)		<1	---

CONTAMINANTS





	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	5	---
Sodium	ppm	ASTM D5185(m)		6	---
Potassium	ppm	ASTM D5185(m)	>20	2	---

FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>5000	● 108457	---	---
Particles >6µm	ASTM D7647	>1300	● 29766	---	---
Particles >14µm	ASTM D7647	>160	▲ 983	---	---
Particles >21µm	ASTM D7647	>40	▲ 119	---	---
Particles >38µm	ASTM D7647	>10	0	---	---
Particles >71µm	ASTM D7647	>3	0	---	---
Oil Cleanliness	ISO 4406 (c)	>19/17/14	● 24/22/17	---	---



OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	Visual*	NONE	NONE	---	---
Yellow Metal	scalar	Visual*	NONE	NONE	---	---
Precipitate	scalar	Visual*	NONE	NONE	---	---
Silt	scalar	Visual*	NONE	NONE	---	---
Debris	scalar	Visual*	NONE	VLITE	---	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---
Emulsified Water	scalar	Visual*	>0.1	NEG	---	---
Free Water	scalar	Visual*		NEG	---	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	23.8	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color		no image	no image
Bottom		no image	no image

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 GFL Environmental - 730 - Chicoutimi - Hauling
Sample No. : GFL0080337 **Received** : 13 Sep 2023 3199 Boul. Talbot
Lab Number : **02582170** **Diagnosed** : 14 Sep 2023 Chicoutimi, QC
Unique Number : 5643235 **Diagnostician** : Kevin Marson CA G7H 5B1
Test Package : MOB 1 (Additional Tests: PrtCount)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Contact: Yan Houde
 yhoude@matrec.ca
 T: (418)549-8074
 F: (418)549-7973