


Area
Cranes [450207985]
 Machine Id
Crane - Fwd Hoisting Winch Gearbox (S/N Sample Tag MA-04003-S5)
 Component
Gearbox
 Fluid
PETRO CANADA GEARLUBE TOS 80W90 (26 LTR)



DIAGNOSIS

Recommendation
 Resample at the next service interval to monitor.

Wear
 All component wear rates are normal.

Contamination
 The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition
 The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PC0076458	PC	PC0040622
Sample Date	Client Info	04 Oct 2023	13 Aug 2023	05 Aug 2023
Machine Age	hrs	0	0	0
Oil Age	hrs	0	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184*	0	0	0
Iron	ppm ASTM D5185(m) >150	5	18	36
Chromium	ppm ASTM D5185(m) >10	0	<1	<1
Nickel	ppm ASTM D5185(m) >10	<1	<1	<1
Titanium	ppm ASTM D5185(m)	0	0	0
Silver	ppm ASTM D5185(m)	<1	0	0
Aluminum	ppm ASTM D5185(m) >5	0	<1	<1
Lead	ppm ASTM D5185(m) >65	0	0	0
Copper	ppm ASTM D5185(m) >80	<1	<1	<1
Tin	ppm ASTM D5185(m) >8	0	0	0
Antimony	ppm ASTM D5185(m) >5	0	0	0
Vanadium	ppm ASTM D5185(m)	0	0	0
Beryllium	ppm ASTM D5185(m)	0	0	0
Cadmium	ppm ASTM D5185(m)	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185(m) 240	264	240	222
Barium	ppm ASTM D5185(m) 1	<1	<1	<1
Molybdenum	ppm ASTM D5185(m) 0.0	0	0	0
Manganese	ppm ASTM D5185(m)	0	<1	1
Magnesium	ppm ASTM D5185(m) 2	<1	1	2
Calcium	ppm ASTM D5185(m) 6	4	4	8
Phosphorus	ppm ASTM D5185(m) 1000	975	1061	1022
Zinc	ppm ASTM D5185(m) 3	13	42	89
Sulfur	ppm ASTM D5185(m) 19400	17499	17695	17469
Lithium	ppm ASTM D5185(m)	<1	<1	<1






CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185(m) >20	10	2	4
Sodium	ppm ASTM D5185(m)	<1	<1	1
Potassium	ppm ASTM D5185(m) >20	0	<1	<1

FLUID CLEANLINESS

method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >20000	123535	49832	74414
Particles >6µm	ASTM D7647 >5000	41403	9025	14849
Particles >14µm	ASTM D7647 >640	201	220	353
Particles >21µm	ASTM D7647 >160	33	28	44
Particles >38µm	ASTM D7647 >40	8	3	1
Particles >71µm	ASTM D7647 >10	5	2	0
Oil Cleanliness	ISO 4406 (c) >21/19/16	24/23/15	23/20/15	23/21/16

OIL ANALYSIS REPORT




FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	1.5	1.68	1.28	1.25

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	VLITE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	140.3	140	140	140
Visc @ 100°C	cSt	ASTM D7279(m)	15.05	14.7	14.8	15.0
Viscosity Index (VI)	Scale	ASTM D2270*	109	104	105	108

SAMPLE IMAGES



Color

Bottom



ISO 17025:2017
Accredited
Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0076458
Lab Number : **02590125**
Unique Number : 5659191
Test Package : MAR 2 (Additional Tests: KV100, PQ, PrtCount, TAN Man, VI)

Received : 18 Oct 2023
Diagnosed : 19 Oct 2023
Diagnostician : Kevin Marson

Suncor - Terra Nova Projects
 Scotia Centre, 235 Water Strret
 St. John's, NL
 CA A1C 1B6
 Contact: Josh Hynes
 joshynes@suncor.com
 T: (709)778-3575
 F: (709)724-2835

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.