

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



HG/NI LAROX #2 HPU

Component

Hydraulic System

PETRO CANADA HYDREX AW 46 (400 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Moor

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

					Sep2023		•
MPLE INFORM	MATION	met	thod	limit/base		current	history1
ole Number		Clien	t Info		PC	0070105	
					_		
ole Date		Clien	t Info		11	Sep 2023	
ine Age	hrs	Clien	t Info		0		

SAMI LE IM ON	/// (1101 4		IIIIII/Dase	Current	HISTORY	HISTOTYZ
Sample Number		Client Info		PC0070105		
Sample Date		Client Info		11 Sep 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>20	1		
Chromium	ppm	ASTM D5185(m)	>20	0		
Nickel	ppm	ASTM D5185(m)	>20	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		<1		
Aluminum	ppm	ASTM D5185(m)	>20	0		
Lead	ppm	ASTM D5185(m)	>20	0		
Copper	ppm	ASTM D5185(m)	>20	1		
Tin	ppm	ASTM D5185(m)	>20	0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	<1		
Barium	ppm	ASTM D5185(m)	0	<1		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)	0	0		
Magnesium	ppm	ASTM D5185(m)	0	0		
Calcium	ppm	ASTM D5185(m)	50	37		
Phosphorus	ppm	ASTM D5185(m)	330	315		
Zinc	ppm	ASTM D5185(m)	430	408		
Sulfur	ppm	ASTM D5185(m)	760	727		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINAN [*]	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	0		
Sodium	ppm	ASTM D5185(m)		<1		
Potassium	ppm	ASTM D5185(m)	>20	0		
FLUID CLEANL	.INESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	2913		
Particles >6µm		ASTM D7647	>1300	681		
Particles >14µm		ASTM D7647	>160	44		
Particles >21µm		ASTM D7647	>40	7		
Particles >38µm		ASTM D7647	>10	1		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/17/13		
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2



OIL ANALYSIS REPORT

