


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
TEAM 15
Machine Id
156108

Component
Gearbox
Fluid
PETRO CANADA ENDURATEX EP 220 (1 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PC0069902	PC0070319	PC0070353
Sample Date	Client Info	25 Oct 2023	12 Apr 2023	15 Feb 2023
Machine Age	mths Client Info	0	0	0
Oil Age	mths Client Info	0	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184*	0	0	0
Iron	ppm ASTM D5185(m) >200	6	16	21
Chromium	ppm ASTM D5185(m) >15	0	0	0
Nickel	ppm ASTM D5185(m) >15	<1	<1	<1
Titanium	ppm ASTM D5185(m)	0	0	0
Silver	ppm ASTM D5185(m)	<1	0	0
Aluminum	ppm ASTM D5185(m) >25	0	0	<1
Lead	ppm ASTM D5185(m) >100	<1	0	0
Copper	ppm ASTM D5185(m) >200	3	6	4
Tin	ppm ASTM D5185(m) >25	0	0	0
Antimony	ppm ASTM D5185(m) >5	0	0	0
Vanadium	ppm ASTM D5185(m)	0	0	0
Beryllium	ppm ASTM D5185(m)	0	0	0
Cadmium	ppm ASTM D5185(m)	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185(m) 60	50	61	64
Barium	ppm ASTM D5185(m) 0	<1	0	0
Molybdenum	ppm ASTM D5185(m) 0	0	0	0
Manganese	ppm ASTM D5185(m) 0	0	<1	<1
Magnesium	ppm ASTM D5185(m) 0	0	0	<1
Calcium	ppm ASTM D5185(m) 0	2	0	1
Phosphorus	ppm ASTM D5185(m) 270	274	298	302
Zinc	ppm ASTM D5185(m) 0	4	5	4
Sulfur	ppm ASTM D5185(m) 11200	5050	5814	5805
Lithium	ppm ASTM D5185(m)	<1	<1	<1





CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185(m) >50	4	6	8
Sodium	ppm ASTM D5185(m)	<1	0	0
Potassium	ppm ASTM D5185(m) >20	0	<1	0

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g ASTM D974* 0.40	0.46	0.45	0.46

OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	220	216	220
Visc @ 100°C	cSt	ASTM D7279(m)	19.35	20.7	19.8
Viscosity Index (VI)	Scale	ASTM D2270*	99	112	103

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS	method	limit/base	current	history1	history2
Ferrous Alloys					
Non-ferrous Metals					
Viscosity @ 40°C					
Acid Number					
PQ					



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0069902 **Received** : 08 Nov 2023
Lab Number : 02595202 **Diagnosed** : 09 Nov 2023
Unique Number : 5672281 **Diagnostician** : Wes Davis
Test Package : IND 2 (Additional Tests: KV100, TAN Man, VI)

Dryden Fibre
 Box 3001, 1 Duke Street
 Dryden, ON
 CA P8N 2Z7
 Contact: Adebukola Adekanye
 AADEKANYE@DRYDENFIBRE.CA
 T: (807)223-9950
 F: (807)223-9176

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.