



Machine Id
CHEVY DURAMAX

Component
Diesel Engine

Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Test for glycol is negative. There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PC0081746	---	---
Sample Date	Client Info			06 Dec 2023	---	---
Machine Age	kms	Client Info		293800	---	---
Oil Age	kms	Client Info		10000	---	---
Oil Changed	Client Info			N/A	---	---
Sample Status				NORMAL	---	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>5		<1.0	---	---
Water	WC Method	>0.2		NEG	---	---


WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>100	6	---	---
Chromium	ppm	ASTM D5185(m)	>20	0	---	---
Nickel	ppm	ASTM D5185(m)	>4	<1	---	---
Titanium	ppm	ASTM D5185(m)		0	---	---
Silver	ppm	ASTM D5185(m)	>3	<1	---	---
Aluminum	ppm	ASTM D5185(m)	>20	3	---	---
Lead	ppm	ASTM D5185(m)	>40	25	---	---
Copper	ppm	ASTM D5185(m)	>330	37	---	---
Tin	ppm	ASTM D5185(m)	>15	<1	---	---
Antimony	ppm	ASTM D5185(m)		0	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---
Beryllium	ppm	ASTM D5185(m)		0	---	---
Cadmium	ppm	ASTM D5185(m)		0	---	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	250	52	---	---
Barium	ppm	ASTM D5185(m)	10	<1	---	---
Molybdenum	ppm	ASTM D5185(m)	100	87	---	---
Manganese	ppm	ASTM D5185(m)		0	---	---
Magnesium	ppm	ASTM D5185(m)	450	35	---	---
Calcium	ppm	ASTM D5185(m)	3000	2049	---	---
Phosphorus	ppm	ASTM D5185(m)	1150	977	---	---
Zinc	ppm	ASTM D5185(m)	1350	1149	---	---
Sulfur	ppm	ASTM D5185(m)	4250	3060	---	---
Lithium	ppm	ASTM D5185(m)		<1	---	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	13	---	---
Sodium	ppm	ASTM D5185(m)	>158	89	---	---
Potassium	ppm	ASTM D5185(m)	>20	16	---	---
Glycol	%	ASTM D7922*		0.0	---	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	>3	0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	9.6	---	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	19.0	---	---

OIL ANALYSIS REPORT













FLUID DEGRADATION	method	limit/base	current	history1	history2	
Oxidation	Abs./1mm	ASTM D7414*	>25	15.4	---	---

VISUAL	method	limit/base	current	history1	history2	
Emulsified Water	scalar	Visual*	>0.2	NEG	---	---
Free Water	scalar	Visual*		NEG	---	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D7279(m)	115	85.6	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	14.4	12.8	---	---
Viscosity Index (VI)	Scale	ASTM D2270*	126	148	---	---

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0081746 **Received** : 07 Dec 2023
Lab Number : **02601474** **Diagnosed** : 08 Dec 2023
Unique Number : 5694559 **Diagnostician** : Kevin Marson
Test Package : MOB 1 (Additional Tests: Glycol, KV40, VI)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Wyatt
 BOX 645
 CORONACH, SK
 CA S0H 0Z0
 Contact: Service Manager
 wyatt2480@hotmail.com
 T: (204)206-0366
 F: