


OIL ANALYSIS REPORT



Scoop 6 Yard LHD6103

Rear Left Wheel Hub

PETRO CANADA TRAXON 80W90 (4 LTR)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The condition of the oil is acceptable for the time in service.

ON 80W90 (4 L	in)		Nov2022	Dec2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PC0074998	PC0051047	
Sample Date		Client Info		02 Dec 2023	16 Nov 2022	
Machine Age	hrs	Client Info		7269	0	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>500	61	45	
Chromium	ppm	ASTM D5185(m)	>8	0	0	
Nickel	ppm	ASTM D5185(m)	>5	<1	<1	
Titanium	ppm	ASTM D5185(m)		0	<1	
Silver	ppm	ASTM D5185(m)		0	0	
Aluminum	ppm	ASTM D5185(m)	>5	<1	<1	
Lead	ppm	ASTM D5185(m)	>5	0	<1	
Copper	ppm	ASTM D5185(m)	>50	5	4	
Tin	ppm	ASTM D5185(m)		0	0	
Antimony	ppm	ASTM D5185(m)	>5	0	0	
Vanadium	ppm	ASTM D5185(m)		0	0	
Beryllium	ppm	ASTM D5185(m)		0	0	
Cadmium	ppm	ASTM D5185(m)		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	243	226	46	
Barium	ppm	ASTM D5185(m)	1	1	2	
Molybdenum	ppm	ASTM D5185(m)		0	<1	
Manganese	ppm	ASTM D5185(m)		<1	<1	
Magnesium	ppm	ASTM D5185(m)	2	1	2	
Calcium	ppm	ASTM D5185(m)	6	16	12	
Phosphorus	ppm	ASTM D5185(m)	987	970	719	
Zinc	ppm	ASTM D5185(m)	1	11	10	
Sulfur	ppm	ASTM D5185(m)	21530	17843	22574	
Lithium	ppm	ASTM D5185(m)		<1	<1	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	6	3	
Sodium	ppm	ASTM D5185(m)		<1	<1	



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	LIGHT	VLITE	
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
Precipitate	scalar	Visual*	NONE	NONE	NONE	
Silt	scalar	Visual*	NONE	NONE	NONE	
Debris	scalar	Visual*	NONE	VLITE	NONE	
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
Appearance	scalar	Visual*	NORML	NORML	NORML	
Odor	scalar	Visual*	NORML	NORML	NORML	
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
Free Water	scalar	Visual*		NEG	NEG	
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	141.0	138	140	
Visc @ 100°C	cSt	ASTM D7279(m)	15.06	14.6	14.6	
Viscosity Index (VI)	Scale	ASTM D2270*	108	105	103	
SAMPLE IMAG	iES	method	limit/base	current	history1	history2
Bottom						no image
GRAPHS						
Iron (ppm)				Lead (ppm)		
T			20	P		
Abnormal			<u>E</u> 10	Abnormal		
27,			22/2	27,		
Nov16			Dec2/23	Nov16/22		
Aluminum (ppm)				Chromium (p	nm)	
			20	***		
Severe Abnormal			<u>E</u> 10	-		
Nov16/2			Dec2/2	Nov16/22		
Copper (ppm)				Silicon (ppm)		
Severe			100			
Abnormal			E.	Severe		
Nov16/22			Dec2/23	Nov16/22		
Viscosity @ 40°C				Additives		
viacosity @ 40 C			2000			



CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No. Lab Number Unique Number : 5697569

: PC0074998 : 02604484

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Recieved

: 20 Dec 2023 Diagnosed

: 20 Dec 2023 Diagnostician : Wes Davis

Test Package : MOB 1 (Additional Tests: KV100, VI) To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Lakeshore Gold Timmins West

Timmins, ON CA

Contact: Adam Koscielak adam.koscielak@HFSinclair.com

T: F: