

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id **413101** Component **Diesel Engine** Fluid

PETRO CANADA DURON XL SYN BLEND 15W40 (--- GAL)

Recommendation
necommenuation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0099531	GFL0091581	GFL0084317
Sample Date		Client Info		17 Dec 2023	23 Oct 2023	09 Aug 2023
Machine Age	hrs	Client Info		2123	53055	1135
Oil Age	hrs	Client Info		0	0	578
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATI	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>80	21	29	35
Chromium	ppm	ASTM D5185(m)	>5	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>2	<1	<1	<1
Titanium	ppm	ASTM D5185(m)		0	0	<1
Silver	ppm	ASTM D5185(m)	>3	0	<1	0
Aluminum	ppm	ASTM D5185(m)	>30	3	4	3
Lead	ppm	ASTM D5185(m)	>30	0	<1	0
Copper	ppm	ASTM D5185(m)	>150	1	2	4
Tin	ppm	ASTM D5185(m)	>5	0	0	<1
Antimony	ppm	ASTM D5185(m)		0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	1	2	2	5
Barium	ppm	ASTM D5185(m)	1	0	<1	<1
Molybdenum	ppm	ASTM D5185(m)	60	58	57	59
Manganese	ppm	ASTM D5185(m)	1	0	0	<1
Magnesium	ppm	ASTM D5185(m)	1010	941	905	949
Calcium	ppm	ASTM D5185(m)	1070	1116	1085	1116
Phosphorus	ppm	ASTM D5185(m)	1150	1003	938	1028
Zinc	ppm	ASTM D5185(m)	1270	1189	1158	1179
Sulfur	ppm	ASTM D5185(m)	2060	2621	2348	2412
Lithium	ppm	ASTM D5185(m)		<1	<1	<1
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>20	3	5	5
Sodium	ppm	ASTM D5185(m)		1	2	2
Potassium	ppm	ASTM D5185(m)	>20	4	4	5
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	>3	0.7	0.8	0.7
Nitration	Abs/cm	ASTM D7624*	>20	8.7	9.8	10.1
Sulfation	Abs/.1mm	ASTM D7415*	>30	21.6	22.0	23.2



OIL ANALYSIS REPORT



FLUID DEGRADATION method Abs/.1mm ASTM D7414* >25 17.2 19.2 20.0 Oxidation Base Number (BN) mg KOH/g ASTM D2896* 9.6 9.94 7.93 8.13 VISUAL NEG NEG NEG Emulsified Water >0.2 scalar Visual* Free Water NEG scalar Visual* NEG NEG **FLUID PROPERTIES** cSt 15.5 14.1 14.1 Visc @ 100°C ASTM D7279(m) 13.8 GRAPHS Iron (ppm) Lead (ppm) 140 Severe 120 60 100 50 80 40 60 20 40 20 20 10 0 0 Aug9/23 Dec17/23 Aluminum (ppm) Chromium (ppm) 60 Sever 50 10 40 E 30 mdd 20 10 n Dec17/23 lec17 Copper (ppm) Silicon (ppm) 30 S Se 250 30 200 la 150 ud 20 100 10 50 0) 0. Dec17/23 5015Cm Viscosity @ 100°C Base Number 10.0 19 Base 18 KOH/a) cSt (100°C) Bu 4 (ase Abnorn 2.0 12 0.0 Aug9/23 0ct23/23 Dec17/23 Aug9/23 1=122/22 7/23 Paris 2/23 Dec1 : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 GFL Environmental - 550 - Rocky View County Recieved : 02 Jan 2024 : GFL0099531 220 Carmek Blvd : 02605731 Diagnosed : 04 Jan 2024 Rocky View County, AB Unique Number : Wes Davis CA T1X 1X1 : 5698816 Diagnostician Test Package : MOB 2 Contact: GFL Calgary calgarymaintenance@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Report Id: GFL550 [WCAMIS] 02605731 (Generated: 01/04/2024 08:44:33) Rev: 1

CALA

ISO 17025:2017 Accredited

Laboratory

Laboratory

Sample No.

Lab Number

Submitted By: GFL Calgary Page 2 of 2

F: (403)369-6163

Т: