




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
433008

Component
Natural Gas Engine

Fluid
PETRO CANADA DURON GEO LD 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0096752	GFL0096748	---
Sample Date	Client Info		27 Nov 2023	06 Nov 2023	---
Machine Age	kms	Client Info	28087	23517	---
Oil Age	kms	Client Info	0	0	---
Oil Changed	Client Info		N/A	N/A	---
Sample Status			NORMAL	NORMAL	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.1	NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185(m)	>50	6	18	---
Chromium	ppm	ASTM D5185(m)	>4	0	<1	---
Nickel	ppm	ASTM D5185(m)	>2	<1	0	---
Titanium	ppm	ASTM D5185(m)		0	0	---
Silver	ppm	ASTM D5185(m)	>3	0	<1	---
Aluminum	ppm	ASTM D5185(m)	>9	2	2	---
Lead	ppm	ASTM D5185(m)	>30	<1	<1	---
Copper	ppm	ASTM D5185(m)	>35	1	3	---
Tin	ppm	ASTM D5185(m)	>4	<1	<1	---
Antimony	ppm	ASTM D5185(m)		0	0	---
Vanadium	ppm	ASTM D5185(m)		0	0	---
Beryllium	ppm	ASTM D5185(m)		0	0	---
Cadmium	ppm	ASTM D5185(m)		0	0	---

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)	50	27	22	---
Barium	ppm	ASTM D5185(m)	5	0	1	---
Molybdenum	ppm	ASTM D5185(m)	50	46	56	---
Manganese	ppm	ASTM D5185(m)	0	0	<1	---
Magnesium	ppm	ASTM D5185(m)	560	518	546	---
Calcium	ppm	ASTM D5185(m)	1510	1482	1486	---
Phosphorus	ppm	ASTM D5185(m)	780	717	702	---
Zinc	ppm	ASTM D5185(m)	870	823	859	---
Sulfur	ppm	ASTM D5185(m)	2040	2072	1998	---
Lithium	ppm	ASTM D5185(m)		<1	<1	---

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m)	>+100	8	21	---
Sodium	ppm	ASTM D5185(m)		4	6	---
Potassium	ppm	ASTM D5185(m)	>20	2	<1	---

INFRA-RED


	method	limit/base	current	history1	history2	
Soot %	%	ASTM D7844*		0	0	---
Nitration	Abs/cm	ASTM D7624*	>20	7.9	9.4	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	19.6	20.2	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	ASTM D7414*	>25	16.4	17.3	---











OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	---
Free Water	scalar	Visual*		NEG	NEG	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	15.1	14.5	14.3	---

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 GFL Environmental - 574 - Vancouver Fleet
Sample No. : GFL0096752 **Received** : 18 Jan 2024
Lab Number : 02609691 **Diagnosed** : 18 Jan 2024
Unique Number : 5710777 **Diagnostician** : Wes Davis
Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Contact: Gary Ewasiuk
 gewasiuk@gflenv.com

T:
 F: