

OIL ANALYSIS REPORT

Machine Id 190 Component

Planetary Fluid

PETRO CANADA TRAXON XL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The condition of the oil is acceptable for the time in service.


SYN BLEND 80W14	0 (2 LTR)			Jan 2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0092248		
Sample Date		Client Info		19 Jan 2024		
Machine Age	hrs	Client Info		10017		
Oil Age	hrs	Client Info		500		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METAL	_S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>500	138		
Chromium	ppm	ASTM D5185(m)	>10	0		
Nickel	ppm	ASTM D5185(m)	>10	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>25	<1		
Lead	ppm	ASTM D5185(m)	>25	<1		
Copper	ppm	ASTM D5185(m)	>75	3		
Tin	ppm	ASTM D5185(m)	>10	<1		
Antimony	ppm	ASTM D5185(m)	>5	4		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	246	247		
Barium	ppm	ASTM D5185(m)	1	0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)	1	1		
Calcium	ppm	ASTM D5185(m)	2	20		
Phosphorus	ppm	ASTM D5185(m)	976	1015		
Zinc	ppm	ASTM D5185(m)	3	10		
Sulfur	ppm	ASTM D5185(m)	15600	16794		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINAN	NTS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	5		
Sodium	ppm	ASTM D5185(m)		<1		
Potassium	ppm	ASTM D5185(m)	>20	1		



OIL ANALYSIS REPORT

cSt

Visc @ 40°C



VISUAL		method				history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.2	NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPE	RTIES	method	limit/base	current	history1	history2

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

252

ASTM D7279(m) 253.0

	GRAPHS		
2000 - E 1000 - 0 -	Iron (ppm) Severe Abnormal	150 T a 100 -	Severe Abnormal
100 - Ed 50 -	Aluminum (ppm) Severe	30 - 20 - 81 10 -	Chromium (ppm)
200 g	Copper (ppm) Severe Abnormal	300 T	Severe Abnormal
350 1 (3-00+) ±83 250 •	Viscosity @ 40°C Abnormal Base Abnormal	1500 - H	Additives Calcium phosphorus
200*	Jan19/24	0-	Jan 19724 - Jan 19724 -



CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No. Lab Number

: GFL0092248

: 02610939 Unique Number : 5720034 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 GFL Environmental - 720 - Lafleche - Landfill Recieved : 24 Jan 2024 Diagnosed

: 24 Jan 2024 Diagnostician : Wes Davis

17125 Lafleche Road, Moose Creek, ON CA K0C 1W0 Contact: Charles Bergeron

cbergeron@gflenv.com T: (613)538-4853

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

F: