



Machine Id
5244
Component
Diesel Engine
Fluid
SAE 5W30 (--- LTR)



DIAGNOSIS

Recommendation
Échantillonner de nouveau l'équipement au prochain intervalle de vidange afin d'en surveiller la condition.

Wear
Les taux de métaux sont typiques d'une première vidange.

Contamination
Il y a une trace d'humidité dans l'huile. Le test de glycol est négatif.

Fluid Condition
Le résultat pour le BN indique que la réserve d'alcalinité est acceptable pour l'huile. L'état de l'huile permet d'en prolonger l'utilisation.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PC0079457	---	---
Sample Date	Client Info		04 Jan 2024	---	---
Machine Age	kms	Client Info	32777	---	---
Oil Age	kms	Client Info	32777	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			MARGINAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	---	---

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185(m)	>100	1	---	---
Chromium	ppm	ASTM D5185(m)	>20	0	---	---
Nickel	ppm	ASTM D5185(m)	>2	0	---	---
Titanium	ppm	ASTM D5185(m)	>2	0	---	---
Silver	ppm	ASTM D5185(m)	>2	0	---	---
Aluminum	ppm	ASTM D5185(m)	>25	1	---	---
Lead	ppm	ASTM D5185(m)	>40	0	---	---
Copper	ppm	ASTM D5185(m)	>330	<1	---	---
Tin	ppm	ASTM D5185(m)	>15	0	---	---
Antimony	ppm	ASTM D5185(m)		0	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---
Beryllium	ppm	ASTM D5185(m)		0	---	---
Cadmium	ppm	ASTM D5185(m)		0	---	---

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)		177	---	---
Barium	ppm	ASTM D5185(m)		0	---	---
Molybdenum	ppm	ASTM D5185(m)		64	---	---
Manganese	ppm	ASTM D5185(m)		0	---	---
Magnesium	ppm	ASTM D5185(m)		477	---	---
Calcium	ppm	ASTM D5185(m)		1146	---	---
Phosphorus	ppm	ASTM D5185(m)		599	---	---
Zinc	ppm	ASTM D5185(m)		690	---	---
Sulfur	ppm	ASTM D5185(m)		2347	---	---
Lithium	ppm	ASTM D5185(m)		<1	---	---






CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m)	>25	10	---	---
Sodium	ppm	ASTM D5185(m)		2	---	---
Potassium	ppm	ASTM D5185(m)	>20	<1	---	---
Water	%	ASTM D6304*	>0.2	▲ 0.199	---	---
ppm Water	ppm	ASTM D6304*	>2000	▲ 1995	---	---
Glycol	%	ASTM D7922*		0.0	---	---

INFRA-RED

	method	limit/base	current	history1	history2	
Soot %	%	ASTM D7844*	>3	0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	5.4	---	---
Sulfation	Abs.1mm	ASTM D7415*	>30	14.1	---	---

OIL ANALYSIS REPORT











FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs./1mm	ASTM D7414*	>25	8.7	---	---
Base Number (BN)	mg KOH/g	ASTM D2896*		7.04	---	---

VISUAL		method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.2	▲ .2%	---	---
Free Water	scalar	Visual*		NEG	---	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	60.0	55.9	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	11.0	9.6	---	---
Viscosity Index (VI)	Scale	ASTM D2270*	177	156	---	---

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0079457 **Received** : 30 Jan 2024
Lab Number : **02612103** **Tested** : 02 Feb 2024
Unique Number : 5721198 **Diagnosed** : 02 Feb 2024 - Bill Quesnel
Test Package : MOB 2 (Additional Tests: Glycol, KF, KV40, VI)

TRANSDEV ST-JEAN
 720 TROTTER
 ST-JEAN-SUR-RICHELIEU, QC
 CA J3B 8T2
 Contact: Eric Breton
 eric.breton@transdev.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T:
F: