

OIL ANALYSIS REPORT

Sample Rating Trend





EX0358 Component

Center Swing Drive

PETRO CANADA TRAXON E SYNTHETIC 80W-140 (5 LTR)

DIAGNOSIS

Recommendation

Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


Additive levels indicate the addition of a different brand, or type of oil. The condition of the oil is acceptable for the time in service.

511111E110 00W-140	(5 בווו)		Jul2023	Feb2024		
SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0092325	GFL0087389	
Sample Date		Client Info		09 Feb 2024	28 Jul 2023	
Machine Age	hrs	Client Info		22386	22000	
Oil Age	hrs	Client Info		22386	1000	
Oil Changed		Client Info		Not Changd	Not Changd	
Sample Status				NORMAL	NORMAL	
CONTAMINATI	ON	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>400	20	33	
Chromium	ppm	ASTM D5185(m)	>10	1	<1	
Nickel	ppm	ASTM D5185(m)	>10	0	<1	
Titanium	ppm	ASTM D5185(m)		0	<1	
Silver	ppm	ASTM D5185(m)		0	0	
Aluminum	ppm	ASTM D5185(m)	>25	1	<1	
Lead	ppm	ASTM D5185(m)	>50	<1	0	
Copper	ppm	ASTM D5185(m)	>200	3	3	
Tin	ppm	ASTM D5185(m)	>10	0	0	
Antimony	ppm	ASTM D5185(m)	>5	0	19	
Vanadium	ppm	ASTM D5185(m)		0	0	
Beryllium	ppm	ASTM D5185(m)		0	0	
Cadmium	ppm	ASTM D5185(m)		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	202	81	280	
Barium	ppm	ASTM D5185(m)	<1	0	<1	
Molybdenum	ppm	ASTM D5185(m)		0	<1	
Manganese	ppm	ASTM D5185(m)		0	<1	
Magnesium	ppm	ASTM D5185(m)	<1	14	3	
Calcium	ppm	ASTM D5185(m)		2807	265	
Phosphorus	ppm	ASTM D5185(m)	1209	659	1158	
Zinc	ppm	ASTM D5185(m)	1	129	11	
Sulfur	ppm	ASTM D5185(m)	20439	3289	19077	
Lithium	ppm	ASTM D5185(m)		<1	<1	
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	3	11	
Sodium	ppm	ASTM D5185(m)		2	<1	
Potassium	ppm	ASTM D5185(m)	>20	2	1	



OIL ANALYSIS REPORT

VISUAL



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	Visual*	NONE	NONE	NONE	
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
	Precipitate	scalar	Visual*	NONE	NONE	NONE	
	Silt	scalar	Visual*	NONE	NONE	NONE	
	Debris	scalar	Visual*	NONE	NONE	NONE	
	Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
	Appearance	scalar	Visual*	NORML	NORML	NORML	
	Odor	scalar	Visual*	NORML	NORML	NORML	
	Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
	Free Water	scalar	Visual*		NEG	NEG	
				11 1.0			
	FLUID PROPE		method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D7279(m)	230	53.6	287	
	SAMPLE IMA	GES	method	limit/base	current	history1	history2
	Color						no image
	Bottom						no image
	GRAPHS						
	Iron (ppm)				Lead (ppm)		
	1000 Severe			20	Severe		
	툞 500 - Abnormal			<u>E</u> 10	Abnormal		
	0				0		
	Jui28/23			Feb 9/24	Jul28/23		
	Jul			臣	Juľ		
	Aluminum (ppm)				Chromium (pp	om)	
	100 Severe			3			
	E 50			۳ ۳ ۳	Abnormal		
	3/23			Feb9/24 -			
	Jul28/23			Feb.0	Jul28/23		
	Copper (ppm)				Silicon (ppm)		
	⁶⁰⁰ T			15	Severe		
	400 - Severe			E 10	0 -		
	Abnormal			- 5	0 - Abnormal		
	U			24	53		
	Jul28/23			Feb9/24	Jul28/23		
	Viscosity @ 40°C				Additives		
	300 Abnormal			300	0 T	1	
				E 200	0 - calcium phosphorus		
	ਲੁੱ 100-			E 200	0 - transmission zinc	Conception and the second second	Wanness, Canal & C. C. Constant & C. C. C.
	0				() 		
	53			Feb9/24	Jul28/23		
	Jul28/23			ц.	ηſ		
Accredited Unique N	ory : WearCheck - C8-117 No. : GFL0092325 nber : 02615439 Imber : 5724534	75 Appleby Recei Teste Diagr	ved :13 d :14		L 5H9 GFL Envi	Мос	afleche - Land Lafleche Roa Dse Creek, O CA K0C 1W
Credited Unique N aboratory Test Pa	ory : WearCheck - C8-117 No. : GFL0092325 nber : 02615439	Recei Teste Diagr	ved :13 d :14 losed :14	gton, ON L7 Feb 2024 Feb 2024 Feb 2024 - V	L 5H9 GFL Envi	17125 L Moo Contact: Cha	afleche - Land Lafleche Roa Dse Creek, C CA K0C 1W

Validity of results and interpretation are based on the sample and information as supplied.

Submitted By: Charles Bergeron Page 2 of 2

F: