




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
GFL216
Machine Id
927066
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0113275	GFL0097538	GFL0099655
Sample Date	Client Info		29 Feb 2024	22 Dec 2023	25 Oct 2023
Machine Age	hrs	Client Info	0	19431	296890
Oil Age	hrs	Client Info	0	575	0
Oil Changed	Client Info		N/A	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >120	9	6	9
Chromium	ppm	ASTM D5185(m) >20	0	0	0
Nickel	ppm	ASTM D5185(m) >5	<1	<1	0
Titanium	ppm	ASTM D5185(m) >2	0	0	0
Silver	ppm	ASTM D5185(m) >2	0	0	<1
Aluminum	ppm	ASTM D5185(m) >20	4	3	3
Lead	ppm	ASTM D5185(m) >40	<1	<1	2
Copper	ppm	ASTM D5185(m) >330	2	<1	3
Tin	ppm	ASTM D5185(m) >15	<1	0	<1
Antimony	ppm	ASTM D5185(m)	0	0	0
Vanadium	ppm	ASTM D5185(m)	0	0	0
Beryllium	ppm	ASTM D5185(m)	0	0	0
Cadmium	ppm	ASTM D5185(m)	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 0	2	2	5
Barium	ppm	ASTM D5185(m) 0	0	0	<1
Molybdenum	ppm	ASTM D5185(m) 60	58	59	71
Manganese	ppm	ASTM D5185(m) 0	0	0	0
Magnesium	ppm	ASTM D5185(m) 1010	956	989	1134
Calcium	ppm	ASTM D5185(m) 1070	1055	1082	1226
Phosphorus	ppm	ASTM D5185(m) 1150	1010	1014	1137
Zinc	ppm	ASTM D5185(m) 1270	1160	1195	1397
Sulfur	ppm	ASTM D5185(m) 2060	2490	2577	2708
Lithium	ppm	ASTM D5185(m)	<1	<1	<1

CONTAMINANTS


	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >25	6	3	5
Sodium	ppm	ASTM D5185(m)	2	3	6
Potassium	ppm	ASTM D5185(m) >20	<1	2	1

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	ASTM D7844* >4	0.1	0.1	0.2
Nitration	Abs/cm	ASTM D7624* >20	8.5	8.6	8.5
Sulfation	Abs.1mm	ASTM D7415* >30	20.2	20.2	20.9



OIL ANALYSIS REPORT











FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs./1mm	ASTM D7414*	>25	17.3	17.6	18.2

VISUAL		method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	15.4	13.5	13.4	13.3

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0113275 **Received** : 01 Mar 2024
Lab Number : **02619182** **Tested** : 01 Mar 2024
Unique Number : 5736292 **Diagnosed** : 01 Mar 2024 - Wes Davis
Test Package : MOB 1

GFL Environmental - 252 - GTA Hauling
 3668 Weston Road
 North York, ON
 CA M9L 1W2
 Contact: Tom Hatzioannidis
 thatzioannidis@gflenv.com
 T: (416)406-2040
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.