


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
Cranes
Machine Id
Crane - Aft - Hoisting Winch (S/N Sample Tag MA-04001-S5)
Component
Winch
Fluid
PETRO CANADA GEARLUBE TOS 80W90 (8 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PC0082751	PC0076379	PC
Sample Date	Client Info	17 Mar 2024	31 Dec 2023	26 Nov 2023
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.2	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184*	0	0	0
Iron	ppm ASTM D5185(m) >30	3	<1	7
Chromium	ppm ASTM D5185(m) >2	0	0	0
Nickel	ppm ASTM D5185(m) >2	<1	0	<1
Titanium	ppm ASTM D5185(m) >2	0	0	0
Silver	ppm ASTM D5185(m) >2	0	0	<1
Aluminum	ppm ASTM D5185(m) >5	<1	<1	2
Lead	ppm ASTM D5185(m) >70	0	0	<1
Copper	ppm ASTM D5185(m) >65	<1	<1	<1
Tin	ppm ASTM D5185(m) >9	0	0	0
Antimony	ppm ASTM D5185(m) >5	0	0	0
Vanadium	ppm ASTM D5185(m)	0	0	0
Beryllium	ppm ASTM D5185(m)	0	0	0
Cadmium	ppm ASTM D5185(m)	0	0	0






ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185(m) 240	249	238	205
Barium	ppm ASTM D5185(m) 1	0	0	<1
Molybdenum	ppm ASTM D5185(m) 0.0	0	0	0
Manganese	ppm ASTM D5185(m)	0	0	0
Magnesium	ppm ASTM D5185(m) 2	<1	<1	<1
Calcium	ppm ASTM D5185(m) 6	2	1	5
Phosphorus	ppm ASTM D5185(m) 1000	1017	981	954
Zinc	ppm ASTM D5185(m) 3	8	2	78
Sulfur	ppm ASTM D5185(m) 19400	17875	17679	16845
Lithium	ppm ASTM D5185(m)	<1	<1	<1

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185(m) >30	2	<1	2
Sodium	ppm ASTM D5185(m)	1	0	1
Potassium	ppm ASTM D5185(m) >20	<1	1	0

OIL ANALYSIS REPORT



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
 Sample No. : PC0082751 Received : 18 Mar 2024
 Lab Number : 02622840 Tested : 19 Mar 2024
 Unique Number : 5747959 Diagnosed : 19 Mar 2024 - Kevin Marson
 Test Package : MAR 2 (Additional Tests: KV100, PQ, PrtCount, TAN Man, VI)
 To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>20000	38187	18955	95685	
Particles >6µm	ASTM D7647	>5000	7584	4269	14526	
Particles >14µm	ASTM D7647	>640	190	27	470	
Particles >21µm	ASTM D7647	>160	42	10	88	
Particles >38µm	ASTM D7647	>40	8	5	4	
Particles >71µm	ASTM D7647	>10	6	3	1	
Oil Cleanliness	ISO 4406 (c)	>21/19/16	22/20/15	21/19/12	24/21/16	

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	1.5	1.46	1.33	1.72

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	140.3	141	141	140
Visc @ 100°C	cSt	ASTM D7279(m)	15.05	14.9	14.7	14.7
Viscosity Index (VI)	Scale	ASTM D2270*	109	106	103	104

SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						
Bottom						