

OIL ANALYSIS REPORT

Area {UNASSIGNED} **Or1987** Component

Front Differential

PETRO CANADA DEXRON GEAR OIL 75W-90 (12 LTR)

DIAGNOSIS

Recommendation

Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

Additive levels indicate the addition of a different brand, or type of oil. The condition of the oil is acceptable for the time in service.






SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0113301		
Sample Date		Client Info		22 Feb 2024		
Machine Age	hrs	Client Info		6443		
Oil Age	hrs	Client Info		6443		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINAT	ION	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG		
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>500	59		
Chromium	ppm	ASTM D5185(m)	>10	<1		
Nickel	ppm	ASTM D5185(m)	>10	0		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>25	0		
Lead	ppm	ASTM D5185(m)	>25	0		
Copper	ppm	ASTM D5185(m)	>100	<1		
Tin	ppm	ASTM D5185(m)	>10	0		
Antimony	ppm	ASTM D5185(m)	>5	20		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	60	198		
Barium	ppm	ASTM D5185(m)	0	<1		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)	0	6		
Calcium	ppm	ASTM D5185(m)	0	21		
Phosphorus	ppm	ASTM D5185(m)	1300	1012		
Zinc	ppm	ASTM D5185(m)	20	16		
Sulfur	ppm	ASTM D5185(m)	24100	18719		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	7		
Sodium	ppm	ASTM D5185(m)		2		
Potassium	ppm	ASTM D5185(m)	>20	0		



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	VLITE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	VLITE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>.2	NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	88.50	336		
SAMPLE IMAG	θES	method	limit/base	current	history1	history2
Color					no image	no image
			111		no mago	no inago
Bottom					no image	no image
GRAPHS						
Iron (ppm)				Lead (ppm)		
) T			150	n:		
			E 100	Severe		
Abnormal			50	Abnormal		
			0	/24		
Feb22/24			Feb22/24	Feb 22/24		
Aluminum (ppm)				Chromium (p	pm)	
Severe			30	Severe		
) + 0			툍 ²⁰	Abnormal		
Abnormal				- Q		
2/24				2/24		
Feb22/24			Feb22/24	Feb 22/24		
Copper (ppm)				Silicon (ppm)		
			300	Severe		
Abnormal			E 200	- 0		
			¹ 00	Abnormal		
2/24			2/24	2/24		
Feb22/24			Feb22/24	Feb22/		
Viscosity @ 40°C				Additives		
T			1500		1	
Akesmal			E 1000	calcium phosphoru	S	*****
			⁶ 500	PROFESSION ZINC		
			2/24	2/24		
Feb22/24			Feb 22/24	Feb22/		
/earCheck - C8-1175 iFL0113301	5 Appleby Receiv		lgton, ON L7L ∣Mar 2024	5H9 GFL Env	ironmental - 720 - 1 17125	Lafleche - Landf Lafleche Road
2623792	Tested		Mar 2024 Mar 2024			ose Creek, O
748911	Diagno		Mar 2024 - W	es Davis	100	CA KOC 1W
IOB 1	Ū					arles Bergero
ntact Customer Servi	ice at 1-80	0-268-213	1.			on@gflenv.coi
accreditation, (m) m						(613)538-485

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

CALA

ISO 17025:2017 Accredited Laboratory

Laboratory

Sample No. Lab Number

Unique Number Test Package

F: