


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area

Aft Machinery Space

Machine Id

Thruster Aft Center - Lubrication System (S/N Sample Tag CL-06001-S1)

Component

Lube System

Fluid

PETRO CANADA ENERGOL GR-XP ISO 150 (5000 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PC0081639	PC0080536	PC
Sample Date	Client Info	31 Mar 2024	29 Jan 2024	04 Jan 2024
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method	>0.05	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184*	0	0	0
Iron	ppm	ASTM D5185(m) >20	1	1
Chromium	ppm	ASTM D5185(m) >10	0	0
Nickel	ppm	ASTM D5185(m) >10	0	<1
Titanium	ppm	ASTM D5185(m)	0	0
Silver	ppm	ASTM D5185(m)	0	0
Aluminum	ppm	ASTM D5185(m) >10	0	<1
Lead	ppm	ASTM D5185(m) >20	0	<1
Copper	ppm	ASTM D5185(m) >20	<1	<1
Tin	ppm	ASTM D5185(m) >10	0	0
Antimony	ppm	ASTM D5185(m)	0	0
Vanadium	ppm	ASTM D5185(m)	0	0
Beryllium	ppm	ASTM D5185(m)	0	0
Cadmium	ppm	ASTM D5185(m)	0	0






ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	2	2
Barium	ppm	ASTM D5185(m)	0	0
Molybdenum	ppm	ASTM D5185(m)	0	0
Manganese	ppm	ASTM D5185(m)	0	0
Magnesium	ppm	ASTM D5185(m)	0	<1
Calcium	ppm	ASTM D5185(m)	2	2
Phosphorus	ppm	ASTM D5185(m)	306	309
Zinc	ppm	ASTM D5185(m)	5	5
Sulfur	ppm	ASTM D5185(m)	7762	8111
Lithium	ppm	ASTM D5185(m)	<1	<1

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >15	<1	2
Sodium	ppm	ASTM D5185(m)	<1	0
Potassium	ppm	ASTM D5185(m) >20	<1	<1

OIL ANALYSIS REPORT




FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>5000	1154	2472	1273	
Particles >6µm	ASTM D7647	>1300	169	530	404	
Particles >14µm	ASTM D7647	>160	6	24	34	
Particles >21µm	ASTM D7647	>40	2	4	8	
Particles >38µm	ASTM D7647	>10	0	1	1	
Particles >71µm	ASTM D7647	>3	0	0	1	
Oil Cleanliness	ISO 4406 (c)	>19/17/14	17/15/10	18/16/12	17/16/12	

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.9	0.53	0.56	0.54

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.05	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	149	141	140	140
Visc @ 100°C	cSt	ASTM D7279(m)	14.5	13.9	13.9	13.9
Viscosity Index (VI)	Scale	ASTM D2270*		94	95	95

SAMPLE IMAGES



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0081639 **Received** : 26 Apr 2024
Lab Number : **02631763** **Tested** : 29 Apr 2024
Unique Number : 5772916 **Diagnosed** : 29 Apr 2024 - Kevin Marson
Test Package : MAR 2 (Additional Tests: KV100, PQ, TAN Man, VI)

Suncor - Terra Nova Projects
 Scotia Centre, 235 Water Street
 St. John's, NL
 CA A1C 1B6
 Contact: Josh Hynes
 joshynes@suncor.com
 T: (709)778-3575
 F: (709)724-2835

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.