OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
[1264883]
Machine Id
101042
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 10W30 (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**GFL0116402**	GFL0107934	---
Sample Date		Client Info		**25 Apr 2024**	05 Feb 2024	---
Machine Age	kms	Client Info		**362935**	21917	---
Oil Age	kms	Client Info		**10893**	500	---
Oil Changed		Client Info		**Changed**	Changed	---
Sample Status				**NORMAL**	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel		WC Method	>5	**<1.0**	<1.0	---
Water		WC Method	>0.2	**NEG**	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>100	**10**	15	---
Chromium	ppm	ASTM D5185(m)	>20	**<1**	1	---
Nickel	ppm	ASTM D5185(m)	>4	**<1**	<1	---
Titanium	ppm	ASTM D5185(m)		**0**	0	---
Silver	ppm	ASTM D5185(m)	>3	**0**	0	---
Aluminum	ppm	ASTM D5185(m)	>20	**2**	4	---
Lead	ppm	ASTM D5185(m)	>40	**0**	0	---
Copper	ppm	ASTM D5185(m)	>330	**2**	1	---
Tin	ppm	ASTM D5185(m)	>15	**0**	0	---
Antimony	ppm	ASTM D5185(m)		**0**	0	---
Vanadium	ppm	ASTM D5185(m)		**0**	0	---
Beryllium	ppm	ASTM D5185(m)		**0**	0	---
Cadmium	ppm	ASTM D5185(m)		**0**	0	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	2	**2**	1	---
Barium	ppm	ASTM D5185(m)	0	**0**	0	---
Molybdenum	ppm	ASTM D5185(m)	50	**61**	60	---
Manganese	ppm	ASTM D5185(m)	0	**<1**	0	---
Magnesium	ppm	ASTM D5185(m)	950	**991**	978	---
Calcium	ppm	ASTM D5185(m)	1050	**1061**	1070	---
Phosphorus	ppm	ASTM D5185(m)	995	**1027**	1040	---
Zinc	ppm	ASTM D5185(m)	1180	**1196**	1204	---
Sulfur	ppm	ASTM D5185(m)	2600	**2525**	2772	---
Lithium	ppm	ASTM D5185(m)		**<1**	<1	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	**2**	5	---
Sodium	ppm	ASTM D5185(m)		**8**	6	---
Potassium	ppm	ASTM D5185(m)	>20	**13**	12	---
Glycol	%	ASTM D7922*		**0.0**	NEG	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	>3	**0**	0	---
Nitration	Abs/cm	ASTM D7624*	>20	**8.2**	8.1	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	**19.4**	19.4	---

OIL ANALYSIS REPORT

Glycol Contamination



FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*	>25	**15.9**	15.6	---

VISUAL		method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.2	**NEG**	NEG	---
Free Water	scalar	Visual*		**NEG**	NEG	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	12.00	**11.2**	11.1	---

FT-IR (Direct Trend)



Viscosity @ 100°C



GRAPHS

Iron (ppm)



Lead (ppm)



Aluminum (ppm)



Chromium (ppm)

Copper (ppm)

Silicon (ppm)

Viscosity @ 100°C



Soot %

ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0116402
Lab Number : 02632501
Unique Number : 5773654
Test Package : MOB 1 (Additional Tests: Glycol)

Received : 01 May 2024
Tested : 01 May 2024
Diagnosed : 01 May 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-268-2131.
Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
Validity of results and interpretation are based on the sample and information as supplied.

GFL Environmental - 350 - Emeral Park Regina
2B Industrial Drive,, Great Plains Industrial Park,
Emerald Park, SK
CA S4L 1B6
Contact: Vaughn Hortness
vhortness@gflenv.com
T: (877)244-9500
F: (306)244-9501