




OIL ANALYSIS REPORT



Machine Id
833062
 Component
Natural Gas Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (24 LTR)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0118913	GFL0094404	---
Sample Date	Client Info		07 May 2024	17 Apr 2024	---
Machine Age	hrs	Client Info	1200	1200	---
Oil Age	hrs	Client Info	0	1200	---
Oil Changed	Client Info		Changed	Changed	---
Sample Status			NORMAL	NORMAL	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.1	NEG	NEG	---

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185(m)	>50	7	41	---
Chromium	ppm	ASTM D5185(m)	>4	0	<1	---
Nickel	ppm	ASTM D5185(m)	>2	0	<1	---
Titanium	ppm	ASTM D5185(m)		0	0	---
Silver	ppm	ASTM D5185(m)	>3	0	0	---
Aluminum	ppm	ASTM D5185(m)	>9	1	4	---
Lead	ppm	ASTM D5185(m)	>30	0	2	---
Copper	ppm	ASTM D5185(m)	>35	2	13	---
Tin	ppm	ASTM D5185(m)	>4	0	1	---
Antimony	ppm	ASTM D5185(m)		0	0	---
Vanadium	ppm	ASTM D5185(m)		0	0	---
Beryllium	ppm	ASTM D5185(m)		0	0	---
Cadmium	ppm	ASTM D5185(m)		0	0	---

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)	50	34	10	---
Barium	ppm	ASTM D5185(m)	5	<1	2	---
Molybdenum	ppm	ASTM D5185(m)	50	53	92	---
Manganese	ppm	ASTM D5185(m)	0	1	9	---
Magnesium	ppm	ASTM D5185(m)	560	578	681	---
Calcium	ppm	ASTM D5185(m)	1510	1481	1455	---
Phosphorus	ppm	ASTM D5185(m)	780	745	715	---
Zinc	ppm	ASTM D5185(m)	870	886	873	---
Sulfur	ppm	ASTM D5185(m)	2040	2051	2091	---
Lithium	ppm	ASTM D5185(m)		<1	<1	---

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m)	>+100	3	19	---
Sodium	ppm	ASTM D5185(m)		2	4	---
Potassium	ppm	ASTM D5185(m)	>20	0	2	---

INFRA-RED



	method	limit/base	current	history1	history2	
Soot %	%	ASTM D7844*		0	0	---
Nitration	Abs/cm	ASTM D7624*	>20	7.1	11.4	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	19.6	24.5	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	ASTM D7414*	>25	15.6	19.8	---











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	15.1	14.4	14.0

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0118913 **Received** : 08 May 2024
Lab Number : 02634045 **Tested** : 08 May 2024
Unique Number : 5775198 **Diagnosed** : 08 May 2024 - Wes Davis
Test Package : MOB 1

GFL Environmental - 222 - Sandhill
 SANDHILL DISPOSAL & RECYCLING DIVIS, 19 COMMERCE ROAD
 ORANGEVILLE, ON
 CA L9W 3X5
 Contact: GLENN COOK
 gcook@gflenv.com
 T: (519)940-4167
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.