


OIL ANALYSIS REPORT

Area
Main Power Generation [450323090]
 Machine Id
Generator - MPG (Port) Lube Oil System (S/N Sample Tag XX-80201-S1)
 Component
Turbine
 Fluid
PETRO CANADA TURBOFLO 32 (8300 LTR)

Sample Rating Trend



DIAGNOSIS

Recommendation
 Resample at the next service interval to monitor.

Wear
 All component wear rates are normal.

Contamination
 The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition
 The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PC	PC	PC
Sample Date	Client Info	23 Apr 2024	03 Apr 2024	26 Mar 2024
Machine Age	hrs Client Info	0	0	0
Oil Age	hrs Client Info	0	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.03	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184*	0	0	0
Iron	ppm ASTM D5185(m) >15	0	0	0
Chromium	ppm ASTM D5185(m) >4	0	0	0
Nickel	ppm ASTM D5185(m) >2	0	0	0
Titanium	ppm ASTM D5185(m)	0	0	0
Silver	ppm ASTM D5185(m)	0	0	0
Aluminum	ppm ASTM D5185(m) >10	0	0	0
Lead	ppm ASTM D5185(m)	0	0	0
Copper	ppm ASTM D5185(m) >5	<1	<1	<1
Tin	ppm ASTM D5185(m) >5	0	0	0
Antimony	ppm ASTM D5185(m)	0	0	0
Vanadium	ppm ASTM D5185(m)	0	0	0
Beryllium	ppm ASTM D5185(m)	0	0	0
Cadmium	ppm ASTM D5185(m)	0	0	0






ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185(m) 0	0	<1	<1
Barium	ppm ASTM D5185(m) 0	0	0	0
Molybdenum	ppm ASTM D5185(m) 0	0	0	0
Manganese	ppm ASTM D5185(m)	0	0	0
Magnesium	ppm ASTM D5185(m) 0	<1	0	0
Calcium	ppm ASTM D5185(m) 0	0	0	0
Phosphorus	ppm ASTM D5185(m) 120	261	268	267
Zinc	ppm ASTM D5185(m) 0.0	<1	1	<1
Sulfur	ppm ASTM D5185(m) 0	680	694	694
Lithium	ppm ASTM D5185(m)	<1	<1	<1

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185(m) >15	0	0	0
Sodium	ppm ASTM D5185(m)	0	0	0
Potassium	ppm ASTM D5185(m) >20	<1	<1	0

OIL ANALYSIS REPORT



FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647			245	2210	485
Particles >6µm	ASTM D7647	>640		59	472	160
Particles >14µm	ASTM D7647	>80		5	26	13
Particles >21µm	ASTM D7647	>20		2	6	4
Particles >38µm	ASTM D7647	>4		1	1	1
Particles >71µm	ASTM D7647	>3		0	0	0
Oil Cleanliness	ISO 4406 (c)	>--/16/13		15/13/10	18/16/12	16/14/11

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.04	0.01	0.04	0.04

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.03	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	34.0	33.8	33.8	33.8
Visc @ 100°C	cSt	ASTM D7279(m)	5.59	5.6	5.6	5.7
Viscosity Index (VI)	Scale	ASTM D2270*	110	102	102	108

SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						
Bottom						
MPC					no image	no image



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC
Lab Number : 02634551
Unique Number : 5775704
Test Package : MAR 2 (Additional Tests: KV100, PQ, TAN Man, VI)
Received : 10 May 2024
Tested : 13 May 2024
Diagnosed : 13 May 2024 - Kevin Marson

Suncor - Terra Nova Projects
 Scotia Centre, 235 Water Street
 St. John's, NL
 CA A1C 1B6
 Contact: Josh Hynes
 joshynes@suncor.com
 T: (709)778-3575
 F: (709)724-2835

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.