


OIL ANALYSIS REPORT









Machine Id FREIGHTLINER 422066

Component
Transmission (Auto)

ALLISON TES 295 (--- GAL)

DIAGNOSIS

Recommendation

Échantillonner de nouveau l'équipement au prochain intervalle de vidange afin d'en surveiller la condition.

Wear

Les taux d'usure de tous les composants sont normaux.

Contamination

Il n'y a aucun indice de contamination dans le fluide.


Fluid Condition

L'état de le fluide est acceptable pour la durée de service.

GAL)				May2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GFL0094610		
Sample Date		Client Info		07 May 2024		
Machine Age	hrs	Client Info		4934		
Oil Age	hrs	Client Info		226		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATI	ION	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>160	27		
Chromium	ppm	ASTM D5185(m)	>5	0		
Nickel	ppm	ASTM D5185(m)	>5	0		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)	>5	0		
Aluminum	ppm	ASTM D5185(m)	>50	11		
Lead	ppm	ASTM D5185(m)	>50	1		
Copper	ppm	ASTM D5185(m)	>225	4		
Tin	ppm	ASTM D5185(m)	>10	<1		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	150	70		
Barium	ppm	ASTM D5185(m)	0	0		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)	0	<1		
Calcium	ppm	ASTM D5185(m)	40	124		
Phosphorus	ppm	ASTM D5185(m)	320	213		
Zinc	ppm	ASTM D5185(m)	5	3		
Sulfur	ppm	ASTM D5185(m)	1050	1393		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>20	4		
Sodium	ppm	ASTM D5185(m)		2		
Potassium	ppm	ASTM D5185(m)	>20	<1		




OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	VLITE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.1	NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	38.9	31.9		

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image
GRAPHS					





CALA ISO 17025:2017 Accredited Laboratory

Laboratory

Sample No. : GFL0094610 Lab Number : 02634657 Unique Number : 5775810

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 GFL Environmental 791MAT - Matane Received : 10 May 2024 **Tested**

Diagnosed

: 13 May 2024 : 13 May 2024 - Wes Davis

29 rue Brilliant Matane, QC CA G4W 0J7 Contact: B Berube

Test Package : MOB 1 To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

bberube@matrec.ca T:

Validity of results and interpretation are based on the sample and information as supplied. Report Id: GFL791MAT [WCAMIS] 02634657 (Generated: 06/18/2024 10:18:11) Rev: 1

Contact/Location: B Berube - GFL791MAT

F: