




OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id
8332
 Component
Hydraulic System
 Fluid
PETRO CANADA HYDREX MV 32 (--- GAL)

DIAGNOSIS

Recommendation

Nous vous recommandons de vérifier tous les endroits par lesquels des contaminants peuvent pénétrer dans le système. Nous vous recommandons de remplacer le filtre et d'utiliser un système de filtrage hors-ligne afin d'améliorer la propreté du fluide. Le reniflard d'air doit être réparé. S'il n'est pas classé, nous vous recommandons de le remplacer par un reniflard à air adapté au micron et / ou au dessicant. Si évalué, nous vous recommandons de réparer / remplacer le reniflard. Échantillonner de nouveau dans 30 à 45 jours afin de contrôler la situation.

Wear

Les taux d'usure de tous les composants sont normaux.

Contamination

Il y a une quantité élevée de matières particulaires (2 à 100 µm de taille) présente dans l'huile.

Fluid Condition

L'huile peut encore servir si la contamination peut être réduite à un niveau acceptable.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	GFL0120745	GFL0026767	GFL0053374
Sample Date	Client Info	06 May 2024	03 Jul 2022	30 Jun 2022
Machine Age	hrs	352460	318167	0
Oil Age	hrs	0	0	0
Oil Changed	Client Info	N/A	N/A	Not Changd
Sample Status		SEVERE	SEVERE	ATTENTION

CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.1	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185(m) >40	13	10	7
Chromium	ppm ASTM D5185(m) >5	2	2	2
Nickel	ppm ASTM D5185(m) >2	0	0	0
Titanium	ppm ASTM D5185(m) >2	0	<1	<1
Silver	ppm ASTM D5185(m)	0	0	0
Aluminum	ppm ASTM D5185(m) >8	1	3	<1
Lead	ppm ASTM D5185(m) >5	0	<1	<1
Copper	ppm ASTM D5185(m) >20	2	4	3
Tin	ppm ASTM D5185(m) >2	0	<1	0
Antimony	ppm ASTM D5185(m) >2	0	<1	0
Vanadium	ppm ASTM D5185(m)	0	0	0
Beryllium	ppm ASTM D5185(m)	0	0	0
Cadmium	ppm ASTM D5185(m)	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185(m) 0	2	6	4
Barium	ppm ASTM D5185(m) 0	2	0	0
Molybdenum	ppm ASTM D5185(m) 0	0	0	0
Manganese	ppm ASTM D5185(m) 1	<1	<1	<1
Magnesium	ppm ASTM D5185(m) 0	19	2	1
Calcium	ppm ASTM D5185(m) 50	75	66	58
Phosphorus	ppm ASTM D5185(m) 330	344	328	317
Zinc	ppm ASTM D5185(m) 430	408	393	392
Sulfur	ppm ASTM D5185(m) 760	908	785	773
Lithium	ppm ASTM D5185(m)	<1	<1	<1

CONTAMINANTS




method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185(m) >20	4	6	1
Sodium	ppm ASTM D5185(m)	4	6	6
Potassium	ppm ASTM D5185(m) >20	2	4	3

FLUID CLEANLINESS

method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >5000	▲ 132639	▲ 166526	● 5284
Particles >6µm	ASTM D7647 >1300	▲ 73533	▲ 91096	1081
Particles >14µm	ASTM D7647 >160	▲ 4114	▲ 5570	69
Particles >21µm	ASTM D7647 >40	▲ 690	▲ 866	18
Particles >38µm	ASTM D7647 >10	▲ 26	▲ 25	1
Particles >71µm	ASTM D7647 >3	1	1	0
Oil Cleanliness	ISO 4406 (c) >19/17/14	▲ 24/23/19	▲ 25/24/20	● 20/17/13




OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	31.9	32.9	31.8

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0120745
Lab Number : 02635695
Unique Number : 5776848
Test Package : MOB 1 (Additional Tests: PrtCount)

GFL Environmental - 747 - GMA - Solid Waste
 4 Chemin du Tremblay,
 Boucherville, QC
 CA J4B 6Z5
Contact: Steve Voyer
 svoyer@matrec.ca

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.