




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
926017-9022

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0030996	GFL0022608	GFL0014091
Sample Date	Client Info		30 Aug 2021	17 Mar 2021	07 Jan 2021
Machine Age	hrs	Client Info	15493	14924	14444
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		Not Changed	Not Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >110	34	5	34
Chromium	ppm	ASTM D5185m >4	2	<1	2
Nickel	ppm	ASTM D5185m >2	0	0	0
Titanium	ppm	ASTM D5185m	5	2	6
Silver	ppm	ASTM D5185m >2	<1	<1	<1
Aluminum	ppm	ASTM D5185m >25	0	0	7
Lead	ppm	ASTM D5185m >45	7	<1	5
Copper	ppm	ASTM D5185m >85	2	<1	1
Tin	ppm	ASTM D5185m >4	<1	<1	0
Antimony	ppm	ASTM D5185m	0	0	7
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	0	0	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	16	19	15
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	61	58	54
Manganese	ppm	ASTM D5185m 0	<1	<1	<1
Magnesium	ppm	ASTM D5185m 1010	856	811	933
Calcium	ppm	ASTM D5185m 1070	1185	1039	1162
Phosphorus	ppm	ASTM D5185m 1150	1012	954	1033
Zinc	ppm	ASTM D5185m 1270	1214	1084	1177
Sulfur	ppm	ASTM D5185m 2060	2460	2580	2438

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >30	7	2	14
Sodium	ppm	ASTM D5185m	6	2	6
Potassium	ppm	ASTM D5185m >20	3	1	4

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.8	0.1	1.2
Nitration	Abs/cm	*ASTM D7624 >20	10.7	5.2	10.7
Sulfation	Abs/.1mm	*ASTM D7415 >30	23	19.1	30.9

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	18.4	13.6	27.8
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	6.2	9.3	5.7











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.0	13.7	13.1

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0030996 **Received** : 02 Sep 2021
Lab Number : 05341189 **Diagnosed** : 03 Sep 2021
Unique Number : 9645228 **Diagnostician** : Wes Davis
Test Package : MOB1+

GFL Environmental - 663 - Lake Ariel (Scranton Hauling)
 17 Industrial Park Rd
 Lake Ariel, PA
 US 18436
 Contact: Eric Merone
 emerone@countyclecycling.net
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)