




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
10771C

Component
Natural Gas Engine

Fluid
PETRO CANADA DURON GEO LD 15W40 (30 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history 1	history 2
Sample Number	Client Info		GFL0047433	GFL0047423	GFL0047425
Sample Date	Client Info		22 Jun 2023	02 Nov 2022	27 Oct 2022
Machine Age	hrs	Client Info	15885	14202	14158
Oil Age	hrs	Client Info	600	600	600
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history 1	history 2
Iron	ppm	ASTM D5185m >50	24	17	13
Chromium	ppm	ASTM D5185m >4	5	2	2
Nickel	ppm	ASTM D5185m >2	1	0	0
Titanium	ppm	ASTM D5185m	<1	0	<1
Silver	ppm	ASTM D5185m >3	0	0	0
Aluminum	ppm	ASTM D5185m >9	8	2	2
Lead	ppm	ASTM D5185m >30	10	2	1
Copper	ppm	ASTM D5185m >35	4	3	2
Tin	ppm	ASTM D5185m >4	3	1	1
Vanadium	ppm	ASTM D5185m	<1	0	<1
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history 1	history 2
Boron	ppm	ASTM D5185m 50	13	15	9
Barium	ppm	ASTM D5185m 5	0	0	2
Molybdenum	ppm	ASTM D5185m 50	69	54	52
Manganese	ppm	ASTM D5185m 0	4	2	1
Magnesium	ppm	ASTM D5185m 560	775	497	472
Calcium	ppm	ASTM D5185m 1510	2096	1918	1818
Phosphorus	ppm	ASTM D5185m 780	981	750	710
Zinc	ppm	ASTM D5185m 870	1239	1003	1003
Sulfur	ppm	ASTM D5185m 2040	3257	2936	2699

CONTAMINANTS

	method	limit/base	current	history 1	history 2
Silicon	ppm	ASTM D5185m >+100	12	10	9
Sodium	ppm	ASTM D5185m	13	7	6
Potassium	ppm	ASTM D5185m >20	2	0	2

INFRA-RED



	method	limit/base	current	history 1	history 2
Soot %	%	*ASTM D7844	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624 >20	12.1	11.4	11.5
Sulfation	Abs/.1mm	*ASTM D7415 >30	27.7	23.1	22.9

FLUID DEGRADATION

	method	limit/base	current	history 1	history 2
Oxidation	Abs/.1mm	*ASTM D7414 >25	23.3	17.4	17.5
Base Number (BN)	mg KOH/g	ASTM D2896 10.2	4.8	5.7	5.0







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history 1	history 2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history 1	history 2	
Visc @ 100°C	cSt	ASTM D445	15.1	14.9	13.6	13.4

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0047433 **Received** : 28 Jun 2023
Lab Number : **05885515** **Diagnosed** : 30 Jun 2023
Unique Number : 10535998 **Diagnostician** : Angela Borella
Test Package : FLEET

GFL Environmental - 030 - Conway Myrtle Beach
 3010 HWY 378
 Conway, SC
 US 29527
 Contact: CHET STROSCHINE
 cstroschine@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)