


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
351 (S/N K7404)

Component
Diesel Engine

Fluid
PETRO CANADA DURON HP 15W40 (--- LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history 1	history 2
Sample Number	Client Info		PCA0044171	PCA0044153	---
Sample Date	Client Info		14 Jun 2023	05 Jan 2022	---
Machine Age	hrs	Client Info	559	229	---
Oil Age	hrs	Client Info	559	229	---
Oil Changed	Client Info		Changed	Changed	---
Sample Status			NORMAL	NORMAL	---

CONTAMINATION

	method	limit/base	current	history 1	history 2
Fuel	WC Method	>5	<1.0	<1.0	---
Glycol	WC Method		NEG	NEG	---

WEAR METALS

	method	limit/base	current	history 1	history 2
Iron	ppm	ASTM D5185m >100	22	26	---
Chromium	ppm	ASTM D5185m >20	<1	1	---
Nickel	ppm	ASTM D5185m >4	0	<1	---
Titanium	ppm	ASTM D5185m	0	<1	---
Silver	ppm	ASTM D5185m >3	0	<1	---
Aluminum	ppm	ASTM D5185m >20	3	5	---
Lead	ppm	ASTM D5185m >40	0	<1	---
Copper	ppm	ASTM D5185m >330	5	18	---
Tin	ppm	ASTM D5185m >15	0	1	---
Antimony	ppm	ASTM D5185m	---	<1	---
Vanadium	ppm	ASTM D5185m	0	<1	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history 1	history 2
Boron	ppm	ASTM D5185m	8	68	---
Barium	ppm	ASTM D5185m	<1	3	---
Molybdenum	ppm	ASTM D5185m	61	50	---
Manganese	ppm	ASTM D5185m	1	4	---
Magnesium	ppm	ASTM D5185m	969	654	---
Calcium	ppm	ASTM D5185m	1166	1591	---
Phosphorus	ppm	ASTM D5185m	1085	1102	---
Zinc	ppm	ASTM D5185m	1323	1278	---
Sulfur	ppm	ASTM D5185m	3761	3277	---

CONTAMINANTS

	method	limit/base	current	history 1	history 2
Silicon	ppm	ASTM D5185m >25	13	53	---
Sodium	ppm	ASTM D5185m	2	7	---
Potassium	ppm	ASTM D5185m >20	19	25	---



INFRA-RED

	method	limit/base	current	history 1	history 2
Soot %	%	*ASTM D7844 >3	0.1	0.1	---
Nitration	Abs/cm	*ASTM D7624 >20	7.0	8.4	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	19.2	21.1	---

FLUID DEGRADATION

	method	limit/base	current	history 1	history 2
Oxidation	Abs/.1mm	*ASTM D7414 >25	15.9	17.8	---
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	10.19	9.03	---









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history 1	history 2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history 1	history 2	
Visc @ 100°C	cSt	ASTM D445	15.6	13.0	12.9	---

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0044171 **Received** : 30 Jun 2023
Lab Number : **05888457** **Diagnosed** : 05 Jul 2023
Unique Number : 10538940 **Diagnostician** : Sean Felton
Test Package : MOB 2

1767 GRIFFIN SHOULS RD
 DADEVILLE, AL
 US 36853
 Contact: RON INGRAM
 ron.ingram@ingrampaving.com
 T: (256)825-6878
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)