


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
HINO 372134

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 10W30 (12 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history 1	history 2
Sample Number	Client Info		PCA0083837	PCA0083868	PCA0061072
Sample Date	Client Info		18 May 2023	25 Jan 2023	15 Jun 2022
Machine Age	mls	Client Info	190238	182939	171227
Oil Age	mls	Client Info	7299	5594	5581
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history 1	history 2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history 1	history 2
Iron	ppm	ASTM D5185m >100	9	12	12
Chromium	ppm	ASTM D5185m >20	2	<1	<1
Nickel	ppm	ASTM D5185m >4	1	<1	0
Titanium	ppm	ASTM D5185m	20	73	0
Silver	ppm	ASTM D5185m >3	2	0	<1
Aluminum	ppm	ASTM D5185m >20	5	2	2
Lead	ppm	ASTM D5185m >40	5	1	<1
Copper	ppm	ASTM D5185m >330	2	<1	<1
Tin	ppm	ASTM D5185m >15	2	<1	<1
Antimony	ppm	ASTM D5185m	---	---	---
Vanadium	ppm	ASTM D5185m	1	<1	0
Cadmium	ppm	ASTM D5185m	2	0	0

ADDITIVES

	method	limit/base	current	history 1	history 2
Boron	ppm	ASTM D5185m 2	14	72	10
Barium	ppm	ASTM D5185m 0	19	0	0
Molybdenum	ppm	ASTM D5185m 50	36	18	58
Manganese	ppm	ASTM D5185m 0	2	<1	<1
Magnesium	ppm	ASTM D5185m 950	606	551	873
Calcium	ppm	ASTM D5185m 1050	947	1664	1151
Phosphorus	ppm	ASTM D5185m 995	756	1015	1011
Zinc	ppm	ASTM D5185m 1180	928	1260	1247
Sulfur	ppm	ASTM D5185m 2600	2844	4151	3768

CONTAMINANTS

	method	limit/base	current	history 1	history 2
Silicon	ppm	ASTM D5185m >25	6	5	3
Sodium	ppm	ASTM D5185m	5	5	4
Potassium	ppm	ASTM D5185m >20	7	1	0



INFRA-RED

	method	limit/base	current	history 1	history 2
Soot %	%	*ASTM D7844 >3	1	0.8	0.8
Nitration	Abs/cm	*ASTM D7624 >20	10.6	10.7	10.3
Sulfation	Abs/.1mm	*ASTM D7415 >30	20.7	20.8	21.1

FLUID DEGRADATION

	method	limit/base	current	history 1	history 2
Oxidation	Abs/.1mm	*ASTM D7414 >25	17.3	16.8	17.7
Base Number (BN)	mg KOH/g	ASTM D2896	8.8	8.1	10.3









OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history 1	history 2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history 1	history 2	
Visc @ 100°C	cSt	ASTM D445	12.00	11.8	12.2	11.7

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0083837 **Received** : 03 Jul 2023
Lab Number : 05888792 **Diagnosed** : 05 Jul 2023
Unique Number : 10539275 **Diagnostician** : Don Baldrige
Test Package : MOB 1 (Additional Tests: TBN)

MILLER TRUCK LEASING #123
 66 KELLER AVENUE
 LANCASTER, PA
 US 17601
 Contact: RON ROBERTS
 roberts@millertransgroup.com
 T: (717)945-6205
 F: (717)945-5818

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)