




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
728006

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (18 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history 1	history 2
Sample Number	Client Info	GFL0086089	GFL0083261	GFL0080856
Sample Date	Client Info	01 Jul 2023	09 Jun 2023	02 May 2023
Machine Age	hrs	13225	12754	12750
Oil Age	hrs	414	258	519
Oil Changed	Client Info	Not Chngd	Changed	Not Chngd
Sample Status		NORMAL	NORMAL	ABNORMAL

CONTAMINATION

method	limit/base	current	history 1	history 2
Fuel	WC Method >5	<1.0	<1.0	<1.0
Glycol	WC Method	NEG	NEG	0.0

WEAR METALS

method	limit/base	current	history 1	history 2
Iron	ppm ASTM D5185m >100	9	26	99
Chromium	ppm ASTM D5185m >20	<1	<1	3
Nickel	ppm ASTM D5185m >4	0	0	<1
Titanium	ppm ASTM D5185m	<1	<1	0
Silver	ppm ASTM D5185m >3	0	0	0
Aluminum	ppm ASTM D5185m >20	3	<1	▲ 8
Lead	ppm ASTM D5185m >40	<1	0	6
Copper	ppm ASTM D5185m >330	1	13	183
Tin	ppm ASTM D5185m >15	<1	<1	2
Vanadium	ppm ASTM D5185m	0	<1	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history 1	history 2
Boron	ppm ASTM D5185m 0	21	11	22
Barium	ppm ASTM D5185m 0	0	0	0
Molybdenum	ppm ASTM D5185m 60	60	60	68
Manganese	ppm ASTM D5185m 0	<1	<1	2
Magnesium	ppm ASTM D5185m 1010	817	799	586
Calcium	ppm ASTM D5185m 1070	1095	1131	1468
Phosphorus	ppm ASTM D5185m 1150	955	903	959
Zinc	ppm ASTM D5185m 1270	1181	1113	1189
Sulfur	ppm ASTM D5185m 2060	3530	3082	2224

CONTAMINANTS

method	limit/base	current	history 1	history 2
Silicon	ppm ASTM D5185m >25	7	10	▲ 56
Sodium	ppm ASTM D5185m	2	5	9
Potassium	ppm ASTM D5185m >20	2	4	41

INFRA-RED



method	limit/base	current	history 1	history 2
Soot %	% *ASTM D7844 >3	0.3	0.8	1.6
Nitration	Abs/cm *ASTM D7624 >20	7.0	9.2	11.8
Sulfation	Abs/.1mm *ASTM D7415 >30	18.3	20.0	22.9

FLUID DEGRADATION

method	limit/base	current	history 1	history 2
Oxidation	Abs/.1mm *ASTM D7414 >25	13.3	16.1	21.7
Base Number (BN)	mg KOH/g ASTM D2896 9.8	8.0	7.3	5.8







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history 1	history 2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history 1	history 2	
Visc @ 100°C	cSt	ASTM D445	15.4	12.8	13.0	13.2

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0086089
Lab Number : 05893197
Unique Number : 10549007
Test Package : FLEET

GFL Environmental - 010 - Stockbridge
 1280 Rum Creek Parkway
 Stockbridge, GA
 US 30281
 Contact: JOSHUA TINKER
 joshuatinker@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)