




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
PETERBILT 821047

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GFL0066202	GFL0066205	GFL0060372
Sample Date	Client Info		19 Jun 2023	17 Apr 2023	10 Jan 2023
Machine Age	hrs	Client Info	4393	4393	4393
Oil Age	hrs	Client Info	500	500	4393
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	---	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >110	20	34	34
Chromium	ppm	ASTM D5185m >4	2	2	2
Nickel	ppm	ASTM D5185m >2	0	0	1
Titanium	ppm	ASTM D5185m	0	0	0
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >25	7	▲ 19	25
Lead	ppm	ASTM D5185m >45	0	0	<1
Copper	ppm	ASTM D5185m >85	0	0	1
Tin	ppm	ASTM D5185m >4	0	0	<1
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	10	20	9
Barium	ppm	ASTM D5185m 0	0	0	0
Molybdenum	ppm	ASTM D5185m 60	64	66	65
Manganese	ppm	ASTM D5185m 0	0	0	<1
Magnesium	ppm	ASTM D5185m 1010	980	952	966
Calcium	ppm	ASTM D5185m 1070	1120	1127	1264
Phosphorus	ppm	ASTM D5185m 1150	1041	1044	1029
Zinc	ppm	ASTM D5185m 1270	1288	1283	1278
Sulfur	ppm	ASTM D5185m 2060	3648	3662	3558

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >30	2	3	6
Sodium	ppm	ASTM D5185m	4	4	4
Potassium	ppm	ASTM D5185m >20	6	27	31

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.5	0.7	0.8
Nitration	Abs/cm	*ASTM D7624 >20	7.2	8.2	9.2
Sulfation	Abs/.1mm	*ASTM D7415 >30	19.9	20.4	20.3

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	15.7	16.3	15.9
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	8.5	8.4	8.6







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	*Visual	NONE	NONE	---	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	---	NONE
Precipitate	scalar	*Visual	NONE	NONE	---	NONE
Silt	scalar	*Visual	NONE	NONE	---	NONE
Debris	scalar	*Visual	NONE	NONE	---	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	---	NONE
Appearance	scalar	*Visual	NORML	NORML	---	NORML
Odor	scalar	*Visual	NORML	NORML	---	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	---	NEG
Free Water	scalar	*Visual		NEG	---	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	13.2	12.6

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0066202
Lab Number : 05896012
Unique Number : 10551822
Test Package : FLEET

GFL Environmental - 904B - Menomonic
 1706 MIDWAY RD
 MENOMONIE, WI
 US 54751
 Contact: ANDY KANE

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (715)202-3420

F: