


# OIL ANALYSIS REPORT

## Sample Rating Trend

**NORMAL**



Area  
**(14249Z) Walgreens**  
Machine Id  
**[Walgreens] 136A61444**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 10W30 (11 GAL)**

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

#### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			<b>PCA0094409</b>	PCA0092028	---
Sample Date	Client Info			<b>03 Jul 2023</b>	09 Mar 2023	---
Machine Age	mls Client Info			<b>369537</b>	353757	---
Oil Age	mls Client Info			<b>369537</b>	353757	---
Oil Changed	Client Info			<b>Changed</b>	Not Changd	---
Sample Status				<b>NORMAL</b>	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method		>2.0	<b>&lt;1.0</b>	<1.0	---
Glycol	WC Method			<b>NEG</b>	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	<b>22</b>	14	---
Chromium	ppm	ASTM D5185m	>20	<b>1</b>	1	---
Nickel	ppm	ASTM D5185m	>4	<b>&lt;1</b>	6	---
Titanium	ppm	ASTM D5185m		<b>0</b>	0	---
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	---
Aluminum	ppm	ASTM D5185m	>20	<b>4</b>	4	---
Lead	ppm	ASTM D5185m	>40	<b>3</b>	0	---
Copper	ppm	ASTM D5185m	>330	<b>6</b>	17	---
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	<1	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	---
Cadmium	ppm	ASTM D5185m		<b>0</b>	0	---



ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	<b>&lt;1</b>	8	---
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	---
Molybdenum	ppm	ASTM D5185m	50	<b>61</b>	57	---
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	---
Magnesium	ppm	ASTM D5185m	950	<b>918</b>	887	---
Calcium	ppm	ASTM D5185m	1050	<b>1131</b>	1077	---
Phosphorus	ppm	ASTM D5185m	995	<b>1010</b>	908	---
Zinc	ppm	ASTM D5185m	1180	<b>1244</b>	1256	---
Sulfur	ppm	ASTM D5185m	2600	<b>2951</b>	3056	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<b>4</b>	6	---
Sodium	ppm	ASTM D5185m		<b>0</b>	2	---
Potassium	ppm	ASTM D5185m	>20	<b>4</b>	8	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	<b>0.7</b>	0.4	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>11.2</b>	9.0	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>23.6</b>	20.1	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>19.0</b>	15.8	---
Base Number (BN)	mg KOH/g	ASTM D2896		<b>6.3</b>	7.6	---





# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.00	<b>11.3</b>	11.1

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0094409 **Received** : 12 Jul 2023  
**Lab Number** : **05896784** **Diagnosed** : 13 Jul 2023  
**Unique Number** : 10552594 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**Transervice - Shop 1367 - Berkeley-Jupiter**  
 15998 Walgreens Drive  
 Jupiter, FL  
 US 33478  
 Contact: Manny Gonzalez  
 egonzalez@transervice.com  
 T: (561)776-0755  
 F: (561)776-0799

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)