

OIL ANALYSIS REPORT

Sample Rating Trend

#2015 Der2013 Aug2020 Feb2022 Nov2022 Jan/023 App2023 Jan/023

NORMAL



429048-402450

Component Discol Engin

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

BAL) w2019 Dec2019 Aug/2020 Feb/2022 Nov/2022 Jan/2023 Apr/2023 Jan/2023 Jan/2023						
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number Sample Date		Client Info		GFL0087234 07 Jul 2023	GFL0083789 21 Jun 2023	GFL0083771 08 Jun 2023
Machine Age	hrs	Client Info		15118	14985	14836
Oil Age	hrs	Client Info		0	600	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINAT	ION	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METAL	S	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>110	8	17	13
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	0	<1
Lead	ppm	ASTM D5185m	>45	1	4	3
Copper	ppm	ASTM D5185m	>85	<1	1	<1
Tin	ppm	ASTM D5185m	>4	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	<1
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	58	67	62
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	965	962	954
Calcium	ppm	ASTM D5185m	1070	1069	1174	1093
Phosphorus	ppm	ASTM D5185m	1150	1005	1092	1054
Zinc	ppm	ASTM D5185m	1270	1237	1296	1286
Sulfur	ppm	ASTM D5185m	2060	3580	3192	3208
CONTAMINAN	TS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	7	6	5
Sodium	ppm	ASTM D5185m		4	<1	2
Potassium	ppm	ASTM D5185m	>20	5	6	5
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2	0.5	0.4
Nitration	Abs/cm	*ASTM D7624	>20	7.9	10.6	9.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.5	23.4	22.1
FLUID DEGRAI	OATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.4	22.0	19.1
		ASTM D2896				
Base Number (BN)	mg KOH/g	ASTIVITIZAGE	9.8	8.8	6.6	8.1



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	ERTIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	13.7	13.7

GRAPHS













Certificate L2367

Laboratory Sample No.

Lab Number **Unique Number**

: GFL0087234 : 05897152 : 10552962 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 13 Jul 2023 Diagnosed : 13 Jul 2023

Diagnostician : Wes Davis GFL Environmental - 836 - Kansas City Hauling 7801 East Truman Road

Kansas City, MO US 64126 Contact: Robert Hart

rhart@gflenv.com T: (580)461-1509

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)