# OIL ANALYSIS REPORT

Sample Rating Trend




**NORMAL**

Machine Id
**427083-402340**
Component
**Diesel Engine**
Fluid
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## DIAGNOSIS

**Recommendation**
Resample at the next service interval to monitor.

**Wear**
All component wear rates are normal.

**Contamination**
There is no indication of any contamination in the oil.

**Fluid Condition**
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| SAMPLE INFORMATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Sample Number | | Client Info | | **GFL0064602** | GFL0045403 | GFL0045438 |
| Sample Date | | Client Info | | **10 Jul 2023** | 31 May 2023 | 10 May 2023 |
| Machine Age | hrs | Client Info | | **17131** | 16844 | 16719 |
| Oil Age | hrs | Client Info | | **287** | 16844 | 16719 |
| Oil Changed | | Client Info | | **Not Changd** | Changed | Not Changd |
| Sample Status | | | | **NORMAL** | NORMAL | SEVERE |

| CONTAMINATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Fuel | | WC Method | >3.0 | **<1.0** | <1.0 | <1.0 |
| Glycol | | WC Method | | **NEG** | NEG | NEG |

| WEAR METALS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Iron | ppm | ASTM D5185m | >120 | **8** | 10 | 41 |
| Chromium | ppm | ASTM D5185m | >20 | **<1** | <1 | 0 |
| Nickel | ppm | ASTM D5185m | >5 | **<1** | 0 | 0 |
| Titanium | ppm | ASTM D5185m | >2 | **0** | 0 | <1 |
| Silver | ppm | ASTM D5185m | >2 | **0** | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | **3** | 3 | ⬢ 79 |
| Lead | ppm | ASTM D5185m | >40 | **<1** | 0 | 0 |
| Copper | ppm | ASTM D5185m | >330 | **<1** | 1 | 3 |
| Tin | ppm | ASTM D5185m | >15 | **<1** | <1 | <1 |
| Vanadium | ppm | ASTM D5185m | | **0** | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | | **0** | 0 | 0 |

| ADDITIVES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Boron | ppm | ASTM D5185m | 0 | **8** | 17 | 10 |
| Barium | ppm | ASTM D5185m | 0 | **2** | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 60 | **62** | 67 | 59 |
| Manganese | ppm | ASTM D5185m | 0 | **<1** | <1 | <1 |
| Magnesium | ppm | ASTM D5185m | 1010 | **872** | 951 | 913 |
| Calcium | ppm | ASTM D5185m | 1070 | **1108** | 1152 | 1117 |
| Phosphorus | ppm | ASTM D5185m | 1150 | **964** | 984 | 947 |
| Zinc | ppm | ASTM D5185m | 1270 | **1203** | 1199 | 1215 |
| Sulfur | ppm | ASTM D5185m | 2060 | **3036** | 3157 | 3089 |

| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Silicon | ppm | ASTM D5185m | >25 | **6** | 8 | ▲ 37 |
| Sodium | ppm | ASTM D5185m | | **2** | 3 | 5 |
| Potassium | ppm | ASTM D5185m | >20 | **2** | 0 | 2 |

| INFRA-RED | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Soot % | % | *ASTM D7844 | >4 | **0.5** | 0.5 | 0.8 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | **7.6** | 8.1 | 8.6 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | **20.2** | 20.4 | 20.4 |

| FLUID DEGRADATION | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | **15.4** | 15.8 | 15.4 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 9.8 | **8.1** | 7.4 | 8.2 |

# OIL ANALYSIS REPORT







| VISUAL | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| White Metal | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Silt | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Debris | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | **NONE** | NONE | NONE |
| Appearance | scalar | *Visual | NORML | **NORML** | NORML | NORML |
| Odor | scalar | *Visual | NORML | **NORML** | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | **NEG** | NEG | NEG |
| Free Water | scalar | *Visual | | **NEG** | NEG | NEG |

| FLUID PROPERTIES | | method | limit/base | current | history1 | history2 |
|---|---|---|---|---|---|---|
| Visc @ 100°C | cSt | ASTM D445 | 15.4 | **13.6** | 13.8 | 13.6 |

## GRAPHS













**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513
**Sample No.** : GFL0064602
**Lab Number** : 05898282
**Unique Number** : 10559638
**Test Package** : FLEET

**Received** : 14 Jul 2023
**Diagnosed** : 17 Jul 2023
**Diagnostician** : Wes Davis

Certificate L2367

*To discuss this sample report, contact Customer Service at 1-800-237-1369.*
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
*Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)*


**GFL environmental - 867 - Trafford (Blount Hauling)**
1130 County Line Rd
Trafford, AL
US 35172
Contact: Jonathan Williams
jonathan.williams@gflenv.com
T:
F: