

# **OIL ANALYSIS REPORT**


#### Sample Rating Trend

# **NORMAL**

# Process Cheese [98316341] **NORTH GRINDER MOTOR**

**Top Thrust Bearing** 

ISO 100 (--- GAL)





### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.


#### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

|                  |          |              |            |             | Jul2023     |             |
|------------------|----------|--------------|------------|-------------|-------------|-------------|
| SAMPLE INFORI    | MATION   | method       | limit/base | current     | history1    | history2    |
| Sample Number    |          | Client Info  |            | PCA0100124  | PCA0088302  | PCA0076151  |
| Sample Date      |          | Client Info  |            | 08 Jul 2023 | 02 Apr 2023 | 10 Dec 2022 |
| Machine Age      | hrs      | Client Info  |            | 0           | 0           | 0           |
| Oil Age          | hrs      | Client Info  |            | 0           | 0           | 0           |
| Oil Changed      |          | Client Info  |            | Changed     | Changed     | Changed     |
| Sample Status    |          |              |            | NORMAL      | NORMAL      | NORMAL      |
| WEAR METAL       | S        | method       | limit/base | current     | history1    | history2    |
| Iron             | ppm      | ASTM D5185m  | >85        | 1           | <1          | <1          |
| Chromium         | ppm      | ASTM D5185m  | >20        | <1          | 0           | 0           |
| Nickel           | ppm      | ASTM D5185m  | >20        | 0           | 0           | 0           |
| Titanium         | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Silver           | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Aluminum         | ppm      | ASTM D5185m  | >40        | 0           | 0           | 0           |
| Lead             | ppm      | ASTM D5185m  | >60        | 0           | 0           | 0           |
| Copper           | ppm      | ASTM D5185m  | >7         | <1          | 0           | <1          |
| Tin              | ppm      | ASTM D5185m  | >40        | 0           | 0           | 0           |
| Vanadium         | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| Cadmium          | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| ADDITIVES        |          | method       | limit/base | current     | history1    | history2    |
| Boron            | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Barium           | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Molybdenum       | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Manganese        | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| Magnesium        | ppm      | ASTM D5185m  |            | 3           | 1           | 2           |
| Calcium          | ppm      | ASTM D5185m  |            | 0           | <1          | 0           |
| Phosphorus       | ppm      | ASTM D5185m  |            | 670         | 548         | 395         |
| Zinc             | ppm      | ASTM D5185m  |            | 0           | 3           | 0           |
| Sulfur           | ppm      | ASTM D5185m  |            | 2014        | 1416        | 924         |
| CONTAMINAN       | TS       | method       | limit/base | current     | history1    | history2    |
| Silicon          | ppm      | ASTM D5185m  | >20        | 5           | <1          | <1          |
| Sodium           | ppm      | ASTM D5185m  |            | 2           | 0           | 0           |
| Potassium        | ppm      | ASTM D5185m  | >20        | 1           | 0           | <1          |
| FLUID CLEAN      | INESS    | method       | limit/base | current     | history1    | history2    |
| Particles >4µm   |          | ASTM D7647   | >1300      | 675         | 808         | 333         |
| Particles >6µm   |          | ASTM D7647   | >320       | 90          | 113         | 44          |
| Particles >14µm  |          | ASTM D7647   | >80        | 8           | 11          | 4           |
| Particles >21µm  |          | ASTM D7647   | >20        | 3           | 2           | 1           |
| Particles >38µm  |          | ASTM D7647   | >4         | 0           | 0           | 0           |
| Particles >71μm  |          | ASTM D7647   | >3         | 0           | 0           | 0           |
| Oil Cleanliness  |          | ISO 4406 (c) | >17/15/13  | 17/14/10    | 17/14/11    | 16/13/9     |
| FLUID DEGRA      | DATION   | method       | limit/base | current     | history1    | history2    |
| Acid Number (AN) | mg KOH/g | ASTM D8045   |            | 0.31        | 0.32        | 0.39        |



## **OIL ANALYSIS REPORT**







Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** 

: PCA0100124 : 05898560

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 14 Jul 2023

Diagnosed : 17 Jul 2023 Diagnostician : Jonathan Hester Test Package : IND 2 (Additional Tests: FilterPatch, PrtCount)

KraftHeinz - Springfield - Plant 8311 PCA 2035 E BENNETT SPRINGFIELD, MO

US 65804

Contact: Service Manager

: 10559916 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: F: