


OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
Rear Load
Machine Id
REL133322
Component
Transmission (Auto)
Fluid
NOT GIVEN (--- GAL)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the fluid is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PCA0090703	PCA0083083	---
Sample Date	Client Info		03 Jul 2023	20 Feb 2023	---
Machine Age	hrs	Client Info	27063	26052	---
Oil Age	hrs	Client Info	26560	24524	---
Oil Changed		Client Info	N/A	N/A	---
Sample Status			NORMAL	ABNORMAL	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >220	74	61	---
Chromium	ppm	ASTM D5185m >2	0	<1	---
Nickel	ppm	ASTM D5185m >5	<1	0	---
Titanium	ppm	ASTM D5185m	<1	<1	---
Silver	ppm	ASTM D5185m >5	0	0	---
Aluminum	ppm	ASTM D5185m >75	26	16	---
Lead	ppm	ASTM D5185m >95	9	6	---
Copper	ppm	ASTM D5185m >60	25	12	---
Tin	ppm	ASTM D5185m >10	2	<1	---
Vanadium	ppm	ASTM D5185m	0	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	77	84	---
Barium	ppm	ASTM D5185m	2	0	---
Molybdenum	ppm	ASTM D5185m	<1	<1	---
Manganese	ppm	ASTM D5185m	<1	2	---
Magnesium	ppm	ASTM D5185m	3	4	---
Calcium	ppm	ASTM D5185m	117	111	---
Phosphorus	ppm	ASTM D5185m	221	216	---
Zinc	ppm	ASTM D5185m	5	24	---
Sulfur	ppm	ASTM D5185m	1879	1581	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	11	8	---
Sodium	ppm	ASTM D5185m	3	3	---
Potassium	ppm	ASTM D5185m >20	1	<1	---



FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.24	1.33	---

VISUAL

	method	limit/base	current	history1	history2
White Metal	scalar	*Visual NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual NONE	NONE	NONE	---
Precipitate	scalar	*Visual NONE	NONE	NONE	---
Silt	scalar	*Visual NONE	LIGHT	NONE	---
Debris	scalar	*Visual NONE	NONE	▲ MODER	---
Sand/Dirt	scalar	*Visual NONE	NONE	NONE	---
Appearance	scalar	*Visual NORML	NORML	NORML	---
Odor	scalar	*Visual NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual >0.1	NEG	NEG	---
Free Water	scalar	*Visual	NEG	NEG	---

OIL ANALYSIS REPORT











FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		33.8	34.0	---

SAMPLE IMAGES		method	limit/base	current	history1	history2
---------------	--	--------	------------	---------	----------	----------

Color		no image	no image	no image
Bottom		no image	no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0090703 **Received** : 14 Jul 2023
Lab Number : 05898736 **Diagnosed** : 17 Jul 2023
Unique Number : 10560092 **Diagnostician** : Wes Davis
Test Package : MOB 2

UMM - Shop 401 - Norton
 186 South Washington Street
 Norton, MA
 US 02766
 Contact: Dave Wilson Jr.
 Dwilson1@win-waste.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: